

Product Information

## VESTAKEEP® Care M33 G HP

### MEDIUM-VISCOSITY, UNREINFORCED POLYETHER ETHER KETONE DESIGNED FOR THE MEDICAL DEVICE INDUSTRY



**VESTAKEEP® Care**-grades are ideal materials for the fabrication of medical devices with short time contact to human blood, tissue or bone for up to 30 days.

VESTAKEEP® Care M33 G-HP is a mediumviscosity, unreinforced polyether ether ketone for injection molding and extrusion. The product is refined by Evonik's special filtration technology. The semi-crystalline polymer features superior thermal and chemical resistance.

Parts made from VESTAKEEP® Care M33G-HP are of low flammability. VESTAKEEP® Care M33 G-HP can be processed by common machines for thermoplastics.

#### Biocompatibility of VESTAKEEP® Care

Biocompatibility was tested following ISO10993-1 recommendations for a surface medical device with up to 30 days body contact.

The material fulfills the requirements of USP<88> class VI.

Tests were performed by independent, certified laboratories.

#### Biocompatibility tests for VESTAKEEP® Care:

#### Processing of VESTAKEEP® Care

VESTAKEEP® Care resins can be processed using all conventional melt processing techniques such as injection moulding, extrusion, and compression moulding.

VESTAKEEP® Care M33 G-HP can be processed by common machines for thermoplastics. We recommend a melt temperature between 360°C and 380°C during the injection molding process. The mold temperature should be within a range of 160°C to 200°C, preferably 180°C.

Our technical experts would appreciate to give you support regarding the special requirements for the processing of VESTAKEEP® Care M33 G-HP.

#### Delivery of VESTAKEEP® Care

VESTAKEEP® Care M33 G-HP is supplied as granules in 25 kg boxes with moisture-proof polyethylene liners.

**Key Features**

**Industrial Sector**  
Medical Devices

**Processing**  
Injection molding

**Delivery form**  
Pellets, Granules

**Resistance to**  
Heat (thermal stability), Fire / burn

**Conformity**  
Biocompatibility, Medical application

**Additives**  
Unfilled

<b>Mechanical properties ISO</b>	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Tensile modulus	<b>522000</b>	psi	ISO 527
Yield stress	<b>14200</b>	psi	ISO 527
Yield strain	<b>5</b>	%	ISO 527
Nominal strain at break, tB	<b>25</b>	%	ISO 527
Charpy impact strength, +23°C	<b>N</b>	ftlb/in <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	<b>N</b>	ftlb/in <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>2.85</b>	ftlb/in <sup>2</sup>	ISO 179/1eA
Type of failure	<b>C</b>	-	-
Charpy notched impact strength, -30°C	<b>2.85</b>	ftlb/in <sup>2</sup>	ISO 179/1eA
Type of failure	<b>C</b>	-	-

<b>Thermal properties</b>	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	<b>3.33E-5</b>	in/in/°F	ISO 11359-1/-2

<b>Physical properties</b>	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1.3</b>	g/cm <sup>3</sup>	ISO 1183
Density	<b>1.3</b>	g/cm <sup>3</sup>	ASTM D 792

Burning Behav.	dry	Unit	Test Standard
Burnin behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>0.1260</b>	in	-
GWFI - thickness tested	<b>37.8</b>	in	-
GWIT - thickness tested	<b>31.5</b>	in	-

Electrical properties	dry	Unit	Test Standard
Volume resistivity, V	<b>&gt;1E13</b>	Ohm*m	IEC 62631-3-1

Rheological properties	dry	Unit	Test Standard
Melt volume-flow rate, MVR	<b>20</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>380</b>	°C	-
Load	<b>5</b>	kg	-
Molding shrinkage, parallel	<b>0.9</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>1.1</b>	%	ISO 294-4, 2577
Mold temperature	<b>356</b>	°F	-

### Characteristics

#### Special Characteristics

Semi-crystalline, Medium viscosity

#### Color

Natural color

#### Regulatory

US Pharmacopeia Class VI conformity

#### Chemical Resistance

General chemical resistance