

Product Information

VESTAKEEP® DC 4460 R

X-RAY OPAQUE, TOOTH-COLORED POLYETHER ETHER KETONE FOR DENTAL APPLICATIONS - STOCKSHAPE



VESTAKEEP® DC4460 R is a tooth-colored polyether ether ketone (PEEK) grade that is especially designed for removable and fixed dentures, crowns and bridges.

VESTAKEEP® DC4460 R contains 6% Barium sulphate to render it x-ray opaque.

Biocompatibility

For VESTAKEEP® DC4460 R, biocompatibility has been tested following ISO 10993-1 recommendations for permanent mucous membrane contact.

The compound composition is optimized for high biocompatibility and superior mechanical, thermal and chemical resistance.

Biocompatibility test reports available for VESTAKEEP® DC4460 R

Standard	Description
ISO 10993-03	Genotoxicity: Salmonella Typhimurium Reverse Mutation Test (Ames Test)
ISO 10993-05	Cytotoxicity: Quantitative Growth Inhibition Test
ISO 10993-10	Irritation: Intracutaneous Reactivity
ISO 10993-10	Sensitization: Local Lymph Node Assay
ISO 10993-11	Acute Systemic Toxicity
ISO 10993-11	Subacute / Subchronic Toxicity 14 days
ISO 10993-18	Extraction Tests
USP Class VI	Acute Systemic Toxicity Intracutaneous Reactivity Muscle Implantation

Delivery

VESTAKEEP® DC4460 R rods are available in following diameter and length.

Dimensions of VESTAKEEP® DC4460 R

Diameter	Standard length
100 mm	1000 mm

Other custom dimensions are available on request.

Key Features

Industrial Sector

Medical Devices

Processing

Machining

Delivery form

Stock shape (rods and plates)

Optics

X-ray opaque

Resistance to

Heat (thermal stability), Hydrolysis / hot water, Wear / abrasion, Fatigue resistance

Conformity

Biocompatibility, Medical application

Mechanical properties ISO

	dry	Unit	Test Standard
Tensile modulus	725000	psi	ISO 527
Yield stress	16000	psi	ISO 527
Yield strain	4.2	%	ISO 527
Nominal strain at break, tB	10	%	ISO 527
Izod Impact notched, 23°C	2.43	ftlb/in ²	ISO 180/1A
Flexural modulus, 23°C	725000	psi	ISO 178
Flexural strength, 23°C	25400	psi	ISO 178

Thermal properties

	dry	Unit	Test Standard
Temp. of deflection under load A, 1.80 MPa	311	°F	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	410	°F	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	635	°F	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	581	°F	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	2.5E-5	in/in/°F	ISO 11359-1/-2

Physical properties

	dry	Unit	Test Standard
Density	1.58	g/cm ³	ISO 1183
Water absorption	0.4	%	Sim. to ISO 62
Density	1.52	g/cm ³	ASTM D 792

Characteristics

Special Characteristics

Semi-crystalline

Regulatory

US Pharmacopeia Class VI conformity

Color

Tooth-colored

Chemical Resistance

Acid resistance, Alkali resistance, Solvent resistance, Grease resistance, Hydrolytically stable, Oxidation resistance, General chemical resistance