

Product Information

VESTAKEEP® L 4000 G

HIGH VISCOSITY, UNREINFORCED POLYETHER ETHER KETONE



VESTAKEEP® L 4000 G is a high viscosity, unreinforced lubricated polyether ether ketone for injection molding and extrusion.

The semi-crystalline polymer features superior, thermal and chemical resistance. Parts made from VESTAKEEP® L4000G are of low flammability.

VESTAKEEP® L 4000 G can be processed by common machines for thermoplastics.

The additional lubrication agent improves the feeding process.

We recommend a melt temperature between 370°C and 380°C during the injection molding process. The mold temperature should be within a range of 160°C to 200°C, preferably 180°C.

VESTAKEEP® L 4000 G is supplied as granules in 25 kg boxes with moisture-proof polyethylene liners.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

Key Features

Industrial Sector

Automotive and Mobility, Energy, Oil and Gas

Conformity

Food contact

Processing

Injection molding, Extrusion

Additives

Unfilled

Delivery form

Pellets, Granules

Mechanical properties ISO

Tensile modulus

dry

522000

Unit

psi

Test Standard

ISO 527

Tensile strength	13900	psi	ISO 527
Yield stress	13600	psi	ISO 527
Yield strain	5	%	ISO 527
Nominal strain at break, tB	30	%	ISO 527
Charpy impact strength, +23°C	N	ftlb/in ²	ISO 179/1eU
Charpy impact strength, -30°C	N	ftlb/in ²	ISO 179/1eU
Charpy notched impact strength, +23°C	3.33	ftlb/in ²	ISO 179/1eA
Type of failure	C	-	-
Charpy notched impact strength, -30°C	2.85	ftlb/in ²	ISO 179/1eA
Type of failure	C	-	-
Flexural modulus, 23°C	500000	psi	ISO 178
Flexural stress at conv. deflection, 23°C	16500	psi	ISO 178
Flexural strength, 23°C	21500	psi	ISO 178
Flexural strain at flexural strength, 23°C	7	%	ISO 178
Flexural stress at break, 23°C	N	psi	ISO 178
Flexural strain at break, 23°C	N	%	ISO 178

Mechanical properties ASTM	dry	Unit	Test Standard
Tensile Modulus, var. test speed	590000	psi	ASTM D 638
Yield stress, var. test speed	14000	psi	ASTM D 638
Yield strain, var. test speed	6.5	%	ASTM D 638
Stress at break, var. test speed	13000	psi	ASTM D 638
Nominal strain at break, var. test speed	75	%	ASTM D 638
tensile modulus, annealed	590000	psi	ASTM D 638
Yield strain, 23°C, annealed	6.4	%	ASTM D 638
Yield stress, 23°C, annealed	14500	psi	ASTM D 638
Nominal strain at break, 23°C, annealed	40	%	ASTM D 638
Flexural Modulus, 23°C, annealed	535000	psi	ASTM D 790

Flexural strength, 23°C, annealed	26000	psi	ASTM D 790
Flexural stress at 5% fiber strain, 23°C, annealed	24000	psi	ASTM D 790

Thermal properties	dry	Unit	Test Standard
Melting temperature	644	°F	ISO 11357-1/-3
Temp. of deflection under load A, 1.80 MPa	311	°F	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	401	°F	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	635	°F	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	581	°F	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	3.33E-5	in/in/°F	ISO 11359-1/-2
Melting Temperature	644	°F	ASTM D 3418

Physical properties	dry	Unit	Test Standard
Density	1.3	g/cm ³	ISO 1183
Water absorption	0.5	%	Sim. to ISO 62
Humidity absorption	0.3	%	Sim. to ISO 62
Density	1.3	g/cm ³	ASTM D 792
Shore D hardness, 1s, annealed	87	-	ASTM D 2240

Burning Behav.	dry	Unit	Test Standard
UL Yellow Card available	yes	-	-
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	0.0630	in	-
Burnin behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.1260	in	-
Oxygen index	38	%	ISO 4589-1/-2
Limiting Oxygen Index	38	%	ASTM D 2863
Hot Wire Ignition (HWI)	1	PLC	IEC 60695-2-20
HWI - thickness tested	0.1260	in	-


Electrical properties	dry	Unit	Test Standard
Volume resistivity, V	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity, E	1E15	Ohm	IEC 62631-3-2
Relative permittivity, 100Hz	2.8	-	IEC 62631-2-1
Relative permittivity, 1MHz	2.8	-	IEC 62631-2-1
Dissipation factor, 1MHz	50	E-4	IEC 62631-2-1
CTI, test solution A, 50 drops value	200	-	IEC 60112
Assessment of the insulation group	III a	-	DIN EN 60664-1
CTI, Performance Level Categories, PLC	3	class	ASTM D 3638

Rheological properties	dry	Unit	Test Standard
Melt volume-flow rate, MVR	12	cm ³ /10min	ISO 1133
Temperature	380	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1	%	ISO 294-4, 2577


Test specimen production	dry	Unit	Test Standard
Injection Molding, melt temperature	716	°F	ISO 294
Injection Molding, mold temperature	356	°F	ISO 294
Injection Molding, injection velocity	7.87	in/s	ISO 294
Injection Molding, pressure at hold	17400	psi	ISO 294

Diagrams

Stress-strain



Secant modulus-strain



Characteristics

Applications

Electrical and Electronical

Processing

Film extrusion, Profile extrusion

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass) (23°C)
- ✓ Citric Acid solution (10% by mass) (23°C)
- ✓ Hydrochloric Acid (36% by mass) (23°C)
- ✗ Nitric Acid (40% by mass) (23°C)
- ✓ Sulfuric Acid (38% by mass) (23°C)
- ✓ Sulfuric Acid (5% by mass) (23°C)
- ✓ Chromic Acid solution (40% by mass) (23°C)

Bases

- ✓ Sodium Hydroxide solution (35% by mass) (23°C)
- ✓ Sodium Hydroxide solution (1% by mass) (23°C)
- ✓ Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

- ✓ Isopropyl alcohol (23°C)
- ✓ Methanol (23°C)
- ✓ Ethanol (23°C)

Hydrocarbons

- ✓ n-Hexane (23°C)
- ✓ Toluene (23°C)
- ✓ iso-Octane (23°C)

Ketones

- ✓ Acetone (23°C)

Ethers

- ✓ Diethyl ether (23°C)

Mineral oils

- ✓ SAE 10W40 multigrade motor oil (23°C)
- ✓ Insulating Oil (23°C)

Standard Fuels

- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)

Salt solutions

- ✓ Sodium Chloride solution (10% by mass) (23°C)
- ✓ Sodium Hypochlorite solution (10% by mass) (23°C)
- ✓ Sodium Carbonate solution (20% by mass) (23°C)
- ✓ Sodium Carbonate solution (2% by mass) (23°C)
- ✓ Zinc Chloride solution (50% by mass) (23°C)

Other

- ✓ Ethyl Acetate (23°C)
- ✓ Hydrogen peroxide (23°C)

- ✓ Ethylene Glycol (50% by mass) in water (108°C)
- ✓ Water (23°C)
- ✓ Deionized water (90°C)

Rheological calculation properties

	dry	Unit	Test Standard
Thermal conductivity of melt	1.25	BTU in/(hr ft ² °F)-	-
Spec. heat capacity of melt	0.793	BTU/(lb·F)	-
Min. mold temperature	320	°F	-
Max. mold temperature	392	°F	-
Min. melt temperature	680	°F	-
Max. melt temperature	716	°F	-