

Product Information

VESTAMID® L-GF30 BK 9.7506

GLASS FIBER-REINFORCED HEAT STABILIZED POLYAMIDE 12

VESTAMID® L-GF30 BK 9.7506 is a glass fiber-reinforced heat stabilized Polyamide 12 for injection molding. The material contains about 30% glass fibers, an ageing protective agent and a processing aid for a fast and even form filling. Due to the reinforcement moldings from this compound exhibit a higher strength and good heat resistance.

Further advantages of VESTAMID® L-GF30 BK 9.7506 are the characterizing properties of PA12, e.g., low water absorption, good dimensional stability and nearly constant mechanical properties at changing ambient humidity.

VESTAMID® L-GF30 BK 9.7506 is supplied as cylindrical granules, ready for processing, in moisture-proof bags.

The use of colorants may change property values.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

Key Features

Industrial Sector

Automotive and Mobility, Sustainable, Industry and Engineering

Sustainability

Sustainable electricity

Processing

Injection molding

Delivery form

Pellets, Granules

Resistance to

Heat (thermal stability), UV / light / weathering, Oil / fuels

Electrical

Insulating

Conformity

Automotive

Additives

Glass fibers

LCA-values	dry	Unit	Test Standard
LCA name of certificate	VESTAMID® L GF medium	-	ISO 14040, 14044
LCA certifier	TÜV Rheinland	-	ISO 14040, 14044
Blue water consumption	23.6	kg	ISO 14040, 14044
Global Warming Potential incl. bio. C incl. LUC	5.1	kg CO ₂ eq./kg	ISO 14040, 14044
Global Warming Potential excl. bio. C incl. LUC	5.1	kg CO ₂ eq./kg	ISO 14040, 14044
Land use (ReCiPe 2016)	0.1	Annual crop eq. y	ISO 14040, 14044
GWP savings as compared to 2023 reference	-2.3	kg CO ₂ eq./kg	ISO 14040, 14044

Mechanical properties ISO	dry / cond	Unit	Test Standard
Tensile modulus	986000 / -	psi	ISO 527
Tensile strength	16500 / -	psi	ISO 527
Yield stress	16500 / -	psi	ISO 527
Yield strain	4 / -	%	ISO 527
Stress at break	16100 / -	psi	ISO 527
Nominal strain at break, tB	5 / -	%	ISO 527
Charpy impact strength, +23°C	40.4 / -	ftlb/in ²	ISO 179/1eU
Type of failure	C / -	-	-
Charpy impact strength, -30°C	47.6 / -	ftlb/in ²	ISO 179/1eU
Type of failure	C / -	-	-
Charpy notched impact strength, +23°C	10.9 / -	ftlb/in ²	ISO 179/1eA
Type of failure	C / -	-	-
Charpy notched impact strength, -30°C	9.99 / -	ftlb/in ²	ISO 179/1eA
Type of failure	C / -	-	-
Flexural modulus, 23°C	906000 / -	psi	ISO 178
Flexural stress at conv. deflection, 23°C	24800 / -	psi	ISO 178
Flexural strength, 23°C	27300 / -	psi	ISO 178

Flexural strain at flexural strength, 23°C	5 / -	%	ISO 178
Flexural stress at break, 23°C	26500 / -	psi	ISO 178
Flexural strain at break, 23°C	6 / -	%	ISO 178

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature	352 / *	°F	ISO 11357-1/-3
Temp. of deflection under load A, 1.80 MPa	329 / *	°F	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	347 / *	°F	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	347 / *	°F	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	347 / *	°F	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	3.33E-5 / *	in/in/°F	ISO 11359-1/-2
Melting Temperature	352	°F	ASTM D 3418

Physical properties	dry / cond	Unit	Test Standard
Density	1.24 / -	g/cm ³	ISO 1183
Water absorption	1.1 / *	%	Sim. to ISO 62
Humidity absorption	0.6 / *	%	Sim. to ISO 62
Density	1.24	g/cm ³	ASTM D 792

Burning Behav.	dry / cond	Unit	Test Standard
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	0.0630 / *	in	-
Burnin behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.1260 / *	in	-

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity, V	1E11 / -	Ohm*m	IEC 62631-3-1
Relative permittivity, 50Hz	4.2 / -	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.4 / -	-	IEC 62631-2-1

Dissipation factor, 50Hz	330 / -	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	230 / -	E-4	IEC 62631-2-1
Dielectric strength, AC, S20/S20, t. 1 mm	940 / -	kV/in	IEC 60243-1
CTI, test solution A, 50 drops value	600 / -	-	IEC 60112
Assessment of the insulation group	I	-	DIN EN 60664-1

Rheological properties	dry / cond	Unit	Test Standard
Melt volume-flow rate, MVR	13 / *	cm ³ /10min	ISO 1133
Temperature	275 / *	°C	-
Load	2.16 / *	kg	-
Molding shrinkage, parallel	0.1 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6 / *	%	ISO 294-4, 2577
Mold temperature	176 / *	°F	-
Melt temperature	482 / *	°F	-

Test specimen production	dry	Unit	Test Standard
Injection Molding, melt temperature	482	°F	ISO 294
Injection Molding, mold temperature	176	°F	ISO 294
Injection Molding, injection velocity	7.87	in/s	ISO 294

Characteristics

Special Characteristics

High heat resistant

Color

Black

Additives

Antioxidant agent, Heat stabilizer, Processing aids