

Product Information

VESTAMID® L-R7-MHI BK

MEDIUM-VISCOSITY, PERMANENTLY ANTISTATIC PA12 RESIN WITH ENHANCED STRENGTH



VESTAMID® L-R7-MHI BK is a medium viscosity, permanently antistatic PA12 resin with enhanced strength, especially at low temperatures. Furthermore it is antistatic and contains a processing aid for a fast and even form filling.

The electrical resistance properties which can be achieved on the moulding depend on the processing conditions.

VESTAMID® L-R7-MHI BK is supplied as cylindrical granules, ready for processing, in moisture-proof bags. The processing temperature during the extrusion process should be within a range of 230°C to 270°C.

Pigmentation may affect values.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

Key Features

Industrial Sector

Sustainable, Industry and Engineering

Delivery form

Pellets, Granules

Sustainability

Sustainable electricity

Electrical

Anti-static, Conductive

Processing

Injection molding

Additives

Lubricant, Release agent

LCA-values

LCA name of certificate

dry

[VESTAMID® L Compound high](#)

Unit

-

Test Standard

ISO 14040, 14044

LCA certifier

[TÜV Rheinland](#)

-

ISO 14040, 14044

Blue water consumption	23.9	kg	ISO 14040, 14044
Global Warming Potential incl. bio. C incl. LUC	5.8	kg CO ₂ eq./kg	ISO 14040, 14044
Global Warming Potential excl. bio. C incl. LUC	5.8	kg CO ₂ eq./kg	ISO 14040, 14044
Land use (ReCiPe 2016)	0.1	Annual crop eq. y	ISO 14040, 14044
GWP savings as compared to 2023 reference	-2.1	kg CO ₂ eq./kg	ISO 14040, 14044

Mechanical properties ISO **dry / cond** **Unit** **Test Standard**

Tensile modulus	215000 / 174000	psi	ISO 527
Tensile strength	5220 / -	psi	ISO 527
Yield stress	5220 / 4930	psi	ISO 527
Yield strain	6 / 10	%	ISO 527
Stress at break	4790 / *	psi	ISO 527
Nominal strain at break, tB	33 / >50	%	ISO 527
Charpy impact strength, +23°C	N / N	ftlb/in ²	ISO 179/1eU
Charpy impact strength, -30°C	N / N	ftlb/in ²	ISO 179/1eU
Charpy notched impact strength, +23°C	20.5 / 16.2	ftlb/in ²	ISO 179/1eA
Type of failure	P / C	-	-
Charpy notched impact strength, -30°C	5.71 / 3.81	ftlb/in ²	ISO 179/1eA
Type of failure	C / C	-	-
Flexural modulus, 23°C	207000 / -	psi	ISO 178
Flexural stress at conv. deflection, 23°C	6240 / -	psi	ISO 178
Flexural strength, 23°C	7540 / -	psi	ISO 178
Flexural strain at flexural strength, 23°C	7 / -	%	ISO 178
Flexural stress at break, 23°C	N / -	psi	ISO 178
Flexural strain at break, 23°C	N / -	%	ISO 178

Thermal properties **dry / cond** **Unit** **Test Standard**

Melting temperature	352 / *	°F	ISO 11357-1/-3
---------------------	----------------	----	----------------

Temp. of deflection under load A, 1.80 MPa	122 / *	°F	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	266 / *	°F	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	347 / *	°F	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	284 / *	°F	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	9.44E-5 / *	in/in/°F	ISO 11359-1/-2
Melting Temperature	352	°F	ASTM D 3418

Physical properties	dry / cond	Unit	Test Standard
Density	1.08 / 1.08	g/cm ³	ISO 1183
Water absorption	1.5 / *	%	Sim. to ISO 62
Humidity absorption	0.7 / *	%	Sim. to ISO 62
Density	1.08	g/cm ³	ASTM D 792

Burning Behav.	dry / cond	Unit	Test Standard
UL Yellow Card available	yes / *	-	-
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	0.0591 / *	in	-
Burnin behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.1181 / *	in	-
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.0295 / *	in	-
Hot Wire Ignition (HWI)	4	PLC	IEC 60695-2-20
HWI - thickness tested	0.0295	in	-
Hot Wire Ignition (HWI)	3	PLC	IEC 60695-2-20
HWI - thickness tested	0.0591	in	-
Hot Wire Ignition (HWI)	3	PLC	IEC 60695-2-20
HWI - thickness tested	0.1181	in	-

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity, V	4.75E7 / -	Ohm*m	IEC 62631-3-1
Surface resistivity, C, circular electrodes	6.4E9 / -	Ohm/sq	IEC 62631-3-2
Surface resistance, RSD	1E7 / -	Ohm	IEC 62631-3-2
Surface resistivity, D	1E8 / -	Ohm/sq	IEC 62631-3-2
Test specimen	UL-Stab /	-	-
CTI, Performance Level Categories, PLC	3	class	ASTM D 3638

Rheological properties	dry / cond	Unit	Test Standard
Melt volume-flow rate, MVR	16 / *	cm ³ /10min	ISO 1133
Temperature	275 / *	°C	-
Load	5 / *	kg	-
Molding shrinkage, parallel	1.4 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.4 / *	%	ISO 294-4, 2577
Mold temperature	176 / *	°F	-
Melt temperature	464 / *	°F	-

Test specimen production	dry	Unit	Test Standard
Injection Molding, melt temperature	482	°F	ISO 294
Injection Molding, mold temperature	176	°F	ISO 294
Injection Molding, injection velocity	7.87	in/s	ISO 294
Injection Molding, pressure at hold	10200	psi	ISO 294

Characteristics

Applications

Encapsulation, IT and telecommunication

Color

Black

Special Characteristics

High impact strength, Light-stabilized, High heat resistant, Medium viscosity

Additives

Release agent, Light stabilizer, Heat stabilizer, Processing aids

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass) (23°C)
- ✓ Citric Acid solution (10% by mass) (23°C)

Bases

- ✓ Sodium Hydroxide solution (35% by mass) (23°C)
- ✓ Sodium Hydroxide solution (1% by mass) (23°C)
- ✓ Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

- ✓ Isopropyl alcohol (23°C)
- ✓ Methanol (23°C)
- ✓ Ethanol (23°C)

Hydrocarbons

- ✓ n-Hexane (23°C)
- ✓ Toluene (23°C)
- ✓ iso-Octane (23°C)

Ketones

- ✓ Acetone (23°C)

Ethers

- ✓ Diethyl ether (23°C)

Mineral oils

- ✓ SAE 10W40 multigrade motor oil (23°C)
- ✓ Insulating Oil (23°C)

Standard Fuels

- ✓ ISO 1817 Liquid 1 (60°C)
- ✓ ISO 1817 Liquid 2 (60°C)
- ✓ ISO 1817 Liquid 3 (60°C)
- ✓ ISO 1817 Liquid 4 (60°C)
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)

- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (90°C)
- ✓ Diesel EN 590 (100°C)

Salt solutions

- ✓ Sodium Chloride solution (10% by mass) (23°C)
- ✓ Sodium Carbonate solution (20% by mass) (23°C)
- ✓ Sodium Carbonate solution (2% by mass) (23°C)
- ✓ Zinc Chloride solution (50% by mass) (23°C)

Other

- ✓ Ethyl Acetate (23°C)
- ✓ Hydrogen peroxide (23°C)
- ✓ DOT No. 4 Brake fluid (120°C)
- ✓ Water (23°C)

Rheological calculation properties

	dry	Unit	Test Standard
Density of melt	57.4	lb/ft ³	-
Thermal conductivity of melt	1.87	BTU in/(hr ft ² °F)	-
Spec. heat capacity of melt	0.992	BTU/(lb·F)	-
Ejection temperature	356	°F	-
Min. mold temperature	86	°F	-
Max. mold temperature	212	°F	-
Min. melt temperature	446	°F	-
Max. melt temperature	518	°F	-