

Product Information

VESTAMID® Terra DS16

MEDIUM-VISCOSITY POLYAMIDE 1010



VESTAMID® Terra DS16 NC is a medium-viscosity PA 1010 basic polymer. VESTAMID® Terra DS16 is semi-crystalline, which is the reason for its high mechanical resistance and chemical stability. It absorbs only little water. As a result its mechanical properties vary little when exposed to changing environmental humidity, and the material features a high dimensional stability.

VESTAMID® Terra DS16 can be used to manufacture films with good transparency.

The high melting point of VESTAMID Terra DS16 compounds results in a high heat deflection temperature that can be advantageous for some applications.

VESTAMID® Terra DS16 occupies a position between the high-performance long-chain polyamides such as PA 12 and PA 1212 and the standard polyamides PA 6 and PA 66, which have a shorter chain length.

VESTAMID® Terra DS16 NC is supplied as cylindrical granules, ready for processing, in moisture-proof bags.

VESTAMID® Terra is a group of new polyamides, the monomers for which are based entirely or partly on renewable raw materials.

VESTAMID® Terra DS is the polycondensation product of 1,10-decamethylene diamine (D) and 1,10-dodecanedioic acid (sebacic acid-S). Because both monomers are extracted from castor oil, VESTAMID® Terra DS is based on natural, bio-based and renewable resources up to 100%.

The results shown have been generated from a low number of production lots. Therefore, they are preliminary and not yet the result of a statistical evaluation. Therefore they must not be used to establish specifications.

Key Features

Industrial Sector

Automotive and Mobility, Optics, Sports and Lifestyle

Optics

X-ray transparent, Opaque

Sustainability

Contains renewable resources

Conformity

Biocompatibility, Contains renewable resources

Processing

Injection molding, Extrusion

Additives

Unfilled

Delivery form
Pellets, Granules

LCA-values	dry	Unit	Test Standard
LCA name of certificate	VESTAMID® TERRA DS	-	ISO 14040, 14044
LCA certifier	TÜV Rheinland	-	ISO 14040, 14044
Blue water consumption	1763.4	kg	ISO 14040, 14044
Global Warming Potential incl. bio. C incl. LUC	5.4	kg CO ₂ eq./kg	ISO 14040, 14044
Global Warming Potential excl. bio. C incl. LUC	7.9	kg CO ₂ eq./kg	ISO 14040, 14044
Land use (ReCiPe 2016)	22.6	Annual crop eq. y	ISO 14040, 14044

Mechanical properties ISO	dry / cond	Unit	Test Standard
Tensile modulus	247000 / 181000	psi	ISO 527
Yield stress	7830 / 6960	psi	ISO 527
Yield strain	5 / 22	%	ISO 527
Stress at 50% strain	* / 5510	psi	ISO 527
Nominal strain at break, tB	>50 / >50	%	ISO 527
Charpy impact strength, +23°C	N / N	ftlb/in ²	ISO 179/1eU
Charpy impact strength, -30°C	N / N	ftlb/in ²	ISO 179/1eU
Charpy notched impact strength, +23°C	3.33 / 3.33	ftlb/in ²	ISO 179/1eA
Type of failure	C / C	-	-
Charpy notched impact strength, -30°C	3.33 / 2.38	ftlb/in ²	ISO 179/1eA
Type of failure	C / C	-	-
Flexural modulus, 23°C	258000 / 178000	psi	ISO 178
Flexural stress at conv. deflection, 23°C	8410 / 5220	psi	ISO 178
Flexural strength, 23°C	10400 / 7250	psi	ISO 178
Flexural strain at flexural strength, 23°C	7 / 9	%	ISO 178

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature	392 / *	°F	ISO 11357-1/-3
Glass transition temperature, DSC	98.6 / *	°F	ISO 11357-1/-2
Temp. of deflection under load A, 1.80 MPa	131 / *	°F	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	277 / *	°F	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	385 / *	°F	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	340 / *	°F	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	6.39E-5 / *	in/in/°F	ISO 11359-1/-2
Coeff. of linear therm. expansion, 23°C to 55 °C, normal	7.5E-5 / *	in/in/°F	ISO 11359-1/-2
Melting Temperature	392	°F	ASTM D 3418

Physical properties	dry / cond	Unit	Test Standard
Density	1.04 / -	g/cm ³	ISO 1183
Water absorption	1.8 / *	%	Sim. to ISO 62
Humidity absorption	1.4 / *	%	Sim. to ISO 62
Density	1.04	g/cm ³	ASTM D 792

Burning Behav.	dry / cond	Unit	Test Standard
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	0.0630 / *	in	-
Burnin behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.1260 / *	in	-

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity, V	>1E13 / 8.3E11	Ohm*m	IEC 62631-3-1
Surface resistivity, C, circular electrodes	>1E15 / >1E15	Ohm/sq	IEC 62631-3-2
Relative permittivity, 50Hz	3.6 / -	-	IEC 62631-2-1
Relative permittivity, 100Hz	3.6 / -	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.1 / -	-	IEC 62631-2-1

VESTAMID® Terra

Dielectric strength, AC, S20/S20, t. 1 mm	940 / -	kV/in	IEC 60243-1
---	----------------	-------	-------------

Rheological properties	dry / cond	Unit	Test Standard
Melt volume-flow rate, MVR	N / A / *	cm ³ /10min	ISO 1133
Molding shrinkage, parallel	1.4 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.5 / *	%	ISO 294-4, 2577

Polymer analytics	dry / cond	Unit	Test Standard
Viscosity number	4430 / *	in ³ /lb	ISO 307, 1157, 1628
biogenic carbon content	100	%	ASTM D 6866

Characteristics

Applications

(Sun-) glasses, Monofilament

Special Characteristics

Halogen-free, Phosphorus-free, PTFE-free, High heat resistant, Medium viscosity

Features

Non-corrosive, Dishwasher detergents resistant

Color

Natural color

Chemical Resistance

General chemical resistance