



TECHNOVINYL POLYMERS(I)LTD.



**TECHNICAL DATA SHEET**

**K-FLEX PVC ELASTOMER  
ELASOMERIC MATT FINISH WIRE & CABLE JACKETING COMPOUND**

PROPERTIES	UNITS	PRODUCT CODE NO.			
		3340	3350	3360	3370
HARDNESS	Shore A	40 (±5)	50 (±5)	60 (±5)	70 (±5)
TENSILE STRENGTH	kg/cm <sup>2</sup>	40	52	63	70
DENSITY	-	1.18	1.19	1.20	1.22
ELONGATION	%	> 400	380	316	280
COLOR	-	Natural			
OZONE RESISTANCE	-	Excellent			
USAGE TEMP.	°C	-25 to +100	-25 to +100	-25 to +100	-25 to +100

**Features:**

- Gel Free Extrusion
- Rubber Looks & Rubber Feel
- Matt Finish
- Good Abrasion Resistance
- Very Good Flexibility
- Soft Touch



TECHNOVINYL POLYMERS(I)LTD.



**TECHNICAL DATA SHEET**

**K-FLEX PVC ELASTOMER  
OIL RESISTANT ELASOMERIC MATT FINISH WIRE & CABLE JACKETING COMPOUND**

PROPERTIES	UNITS	PRODUCT CODE NO.			
		3340 OR	3350 OR	3360 OR	3370 OR
HARDNESS	Shore A	40 (±5)	50 (±5)	60 (±5)	70 (±5)
TENSILE STRENGTH	kg/cm <sup>2</sup>	48	57	69	77
DENSITY	-	1.17	1.18	1.19	1.20
ELONGATION	%	430	400	340	320
COLOR	-	Natural			
OZONE RESISTANCE	-	Excellent			
USAGE TEMP.	°C	-25 to +100	-25 to +100	-25 to +100	-25 to +100

**Features:**

- Oil Resistant
- Gel Free Extrusion
- Rubber Looks & Rubber Feel
- Matt Finish
- Good Abrasion Resistance
- Very Good Flexibility
- Soft Touch