



TECHNOVINYL POLYMERS(I)LTD.



TECHNICAL DATA SHEET

Product Code No.: KPP 7072

**Binary reinforced PP Composite
For Pillar Trims of Automotive interiors**

Properties	Method	Unit	Values
MFR @ 230°C, 2.16 Kg.	ASTM D 1238	Gms/10 min	> 7
Specific gravity	ASTM D 792	g/cm ³	0.99
Tensile Strength @ yield	ASTM D 638	Kg/cm ²	430
Flexural Modulus	ASTM D 790	Kg/cm ²	22800
Notched Izod Impact - at 23°C	ASTM D 256	Kg cm/cm	4
Rockwell Hardness		R-scale	118
HDT @ 0.46 N/mm ²	ASTM D 648	Deg. C	140
Long term Heat Resistance		Deg. C	> 125
Shrinkage Value		%	< 1

Features:

- High Stiffness
- Very High Long term Heat Resistance
- Low Warpage
- UL 94 HB Class & cUL/RTI
- Fast Moulding Cycles
- Medium Flow
- High HDT
- Scratch Resistance
- High Surface Hardness
- High Crystallization Temperature

Applications – Pillar trims for Automotive interiors