



**GRADE: ORION® PCQP7060R, UV, RUV**

Molding Grade: FR w/ Release, w/ UV, w/ UV and Release

**Typical Material Properties**

Physical	Nominal Values	ASTM Test
Specific Gravity	1.26	D792
Melt Flow (300°C/1.2 kg)	12.0 g/10 min	D1238
<b>Mechanical</b>		
Tensile Modulus	480,000 psi	D638
Tensile Strength @ Yield	9,400 psi	D638
Flexural Modulus	490,000 psi	D790
Flexural Strength @ Yield	14,500 psi	D790
<b>Impact</b>		
Notched Izod Impact (73°F, 0.125 in)	2.5 ft-lb/in	D256
<b>Thermal</b>		
DTUL @ 264 psi – Unannealed (0.125 in)	288 °F	D648
<b>Mold Shrinkage</b>		
Linear Flow	.003 - .005 in/in	D955
<b>UL Rating</b>		
Flammability	(f1)	<b>UL746C</b>
RTI	V-0 @ 1.5mm, 5VA @ 2.4mm 125°C, 115°C, 125°C	UL 94 UL746B

**Recommended Processing Guidelines**

	Nominal Values
Drying Time and Temperature	4.0 hrs at 250°F
Suggested Max Moisture	0.020%
Rear Temperature	520 – 550°F
Middle Temperature	530 – 570°F
Front Temperature	550 – 600°F
Nozzle Temperature	550 – 600°F
Processing (Melt) Temperature	550 – 610°F
Mold Temperature	150 – 220°F
Back Pressure	50 – 100 psi
Screw Speed	40 – 75 RPM