



TechnoCompound

Creativity & Innovation in Plastics

TechnoFin PP GF 30 2 N 22 (50792)

Farbe / Colour: schwarz / black
Einsatzgebiet / Use: Spritzgießen / Injection molding

Eigenschaft / Property	Prüfbedingungen / Test condition	Einheit / Unit	Wert / Value
Dichte / Density	ISO 1183	g/cm ³	1,12
MVR	ISO 1133 / 230°C/2,16	cm ³ /10min	22
Glührückstand / Ash content	ISO 3451 (625°C)	%	30
Zug E-Modul / Tensile Modules	ISO 527	MPa	5200
Streckspannung / Tensile Strenght at yield	ISO 527	MPa	60
Streckdehnung / Tensile strain at yield	ISO 527	%	2,5
Charpy Schlagzähigkeit / Charpy impact strength	ISO 179 1eU 23°C	kJ/m ²	30

Verarbeitungsempfehlungen / Processing recommendation

Vortrocknung / Drying process	°C / h	80 / 2 - 4
Werkzeugtemperatur / Tool temperature	°C	30 - 60
Verarbeitungstemperatur / Processing temperature	°C	220 - 280