



**TRIVALENCE**

# TriLON™ 61AG30LV (U,L,HS,NC)

**Polyamide Nylon 6**

## General Information

### Product Description

Low Viscosity, 30% Glass Fiber Reinforced Nylon 6 offered with various additives

#### FEATURES

-Good Strength -Oil/Solvent Resistant  
 -Fast Cyling -High Rigidity  
 -Excellent Chemical Resistance  
 -Great Surface  
 -30% Glass Fiber Reinforced

#### ADDITIONAL FORMULAS

-Added Lubricant "L"  
 -Additional UV "U"  
 -Additonal Heat Stabilizers "HS"  
 -Nucleated "N"

#### COLOR

-All  
 -Translucent/Opaque

### General

<b>Typical Applications</b>	-Appliance, automotive, general, pumps, impellers, housings
<b>Processing Method</b>	-Injection
<b>Form(s)</b>	-Pellets
<b>Compliance</b>	-RoHS Compliant - TVT
<b>Availability</b>	-North America, Europe, Latin America

## ASTM / ISO Properties<sup>1</sup>

Physical	Nominal Value Unit	Test Method
Density	1.36 g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.2mm)	0.4 to 0.7 %	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass	TVT Internal
Mechanical	Nominal Value Unit	Test Method
Tensile Strength, brk	25,000 psi	ASTM D638
Tensile Strain	>4 %	ASTM D638
Flexural Modulus	1200000 psi	ASTM D790
Notched Izod Impact	2.4 ft-lbs/in	ASTM D256
Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	420 °F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	400 °F	ASTM D648
Melting Point	428 °F	TVT Internal
Flammability	Nominal Value Unit	Test Method
0.06 in	HB	UL94 - TVT Internal

### Recommended Processing Guidance

Drying Temperature	150 to 175 °F
Drying Time - DESSICANT	3 to 6 Hours
Suggested Max Moisture	0.2 %
Processing Melt Temperature	530 to 560 °F
Mold Temperature	140 to 200 °F