



**TRIVALENCE**

# TriLON™ 62CG33 (U,L,HS,N)

**Polyamide Nylon 6**

## General Information

### Product Description

33% Glass Fiber Reinforced Nylon 6 offered with various additives.

#### FEATURES

-Superior Strength -Oil/Solvent Resistant  
 -Fast Cyling -High Rigidity  
 -Excellent Chemical Resistance  
 -Gasoline Resistant  
 -33% Glass Fiber Reinforced

#### ADDITIONAL FORMULAS

-Added Lubricant "L"  
 -Additional UV "U"  
 -Additional Heat Stabilizers "HS"  
 -Nucleated "N"

#### COLOR

-All  
 -Translucent/Opaque

### General

<b>Typical Applications</b>	-Appliance, automotive, general, pumps, impellers, housings
<b>Processing Method</b>	-Injection
<b>Form(s)</b>	-Pellets
<b>Compliance</b>	-RoHS Compliant - TVT
<b>Availability</b>	-North America, Europe, Latin America

## ASTM / ISO Properties<sup>1</sup>

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density	1.38	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.5	%	ASTM D955
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal
<b>Mechanical</b>			
Tensile Strength, brk	19,000	psi	ASTM D638
Tensile Strain	>3	%	ASTM D638
Flexural Modulus	950000	psi	ASTM D790
Notched Izod Impact	1.8	ft-lbs/in	ASTM D256
<b>Thermal</b>			
Deflection Temperature Under Load (0.45 MPa)	385	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	375	°F	ASTM D648
Melting Point	430	°F	TVT Internal
<b>Flammability</b>			
0.06 in	HB		UL94 - TVT Internal

### Recommended Processing Guidance

Drying Temperature	170 to 190 °F
Drying Time - DESSICANT	3 to 6 Hours
Suggested Max Moisture	0.2 %
Processing Melt Temperature	480 to 530 °F
Mold Temperature	130 to 195 °F