



TRIVALENCE

TriLON™ 62G20 (U,L,HS,N) ISO

Polyamide Nylon 6

General Information

Product Description

General purpose, 20% Glass Fiber Reinforced Nylon 6 offered with various additives

FEATURES

-Good Strength -Oil/Solvent Resistant
 -Fast Cyling -High Rigidity
 -Excellent Chemical Resistance
 -Gasoline Resistant
 -20% Glass Fiber Reinforced

ADDITIONAL FORMULAS

-Added Lubricant "L"
 -Additional UV "U"
 -Additonal Heat Stabilizers "HS"
 -Nucleated "N"

COLOR

-All
 -Translucent/Opaque

General

Typical Applications -Appliance, automotive, general, pumps, impellers, housings
Processing Method -Injection
Form(s) -Pellets
Compliance -RoHS Compliant - TVT
Availability -North America, Europe, Latin America

ASTM / ISO Properties¹

	Nominal Value	Unit	Test Method
Physical			
Density	1.26	g/cm ³	ISO 1183A
Molding Shrinkage - Flow (3.2mm)	0.4 to 0.8	%	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal
Mechanical			
Tensile Strength, brk	115	MPa	ISO 527
Tensile Strain	>3	%	ISO 527
Tensile Modulus	6400	MPa	ISO 527
Charpy Notched 23°C	5	kJ/m ²	ISO 179
Flex Modulus	5000	MPa	ISO 178
Thermal			
Deflection Temperature Under Load (1.8 MPa)	212	°C	ISO 75
Melting Point	220	°C	TVT Internal
Flammability			
0.06 in	HB		UL94

Recommended Processing Guidance

Drying Temperature 150 to 175 °F
 Drying Time - DESSICANT 3 to 6 Hours
 Suggested Max Moisture 0.2 %
 Processing Melt Temperature 540 to 570 °F
 Mold Temperature 140 to 200 °F