



TRIVALENCE

TriLON™ 64 (HS) ISO

Polyamide Nylon 6

General Information

Product Description

General purpose, Nylon 6 Impact Modified offered with various additives

FEATURES

- Superior Impact -Oil/Solvent Resistant
- Fast Cyling
- Excellent Chemical Resistance
- Gasoline Resistant
- Low Temp Impact

ADDITIONAL FORMULAS

- Added Lubricant "L"
- Additional UV "U"
- Additonal Heat Stabilizers "HS"
- Nucleated "N"

COLOR

- All
- Translucent/Opaque

General

Typical Applications	-Appliance, automotive, general, pumps, impellers, housings
Processing Method	-Injection
Form(s)	-Pellets
Compliance	-RoHS Compliant - TVT
Availability	-North America, Europe, Latin America

ASTM / ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.08	g/cm ³	ISO 1183A
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, brk	50	MPa	ISO 527
Tensile Strain	>5	%	ISO 527
Flexural Modulus	2000	MPa	ISO 178
Charpy Notched 23°C	65	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (.45 MPa)	125	°C	ISO 75
Melting Point	220	°C	TVT Internal
Flammability	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 - TVT Internal

Recommended Processing Guidance

Drying Temperature	150 to 175 °F
Drying Time - DESSICANT	3 to 6 Hours
Suggested Max Moisture	0.2 %
Processing Melt Temperature	540 to 570 °F
Mold Temperature	140 to 200 °F