



TRIVALENCE

TriLON™ 661BG23 (U,L,HS,N)

Polyamide Nylon 66

General Information

Product Description

General purpose, 23% Glass Fiber Reinforced Nylon 66 offered with various additives.

FEATURES

-Great Strength -Oil/Solvent Resistant
 -Fast Cyling -High Rigidity
 -Excellent Chemical Resistance
 -Gasoline Resistant
 -23% Glass Fiber Reinforced

ADDITIONAL FORMULAS

-Added Lubricant "L"
 -Additional UV "U"
 -Additonal Heat Stabilizers "HS"
 -Nucleated "N"

COLOR

-All
 -Translucent/Opaque

General

Typical Applications -Appliance, automotive, general, pumps, impellers, housings
Processing Method -Injection
Form(s) -Pellets
Compliance -RoHS Compliant - TVT
Availability -North America, Europe, Latin America

ASTM / ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.2mm)	0.4 to 0.7	%	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, yld	21000	psi	ASTM D638
Tensile Strain	>3	%	ASTM D638
Flexural Modulus	900000	psi	ASTM D790
Notched Izod Impact	1.1	ft-lbs/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	500	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	469	°F	ASTM D648
Melting Point	504	°F	TVT Internal
Flammability	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 - TVT Internal

Recommended Processing Guidance

Drying Temperature 150 to 175 °F
 Drying Time - DESSICANT 3 to 6 Hours
 Suggested Max Moisture 0.2 %
 Processing Melt Temperature 540 to 570 °F
 Mold Temperature 140 to 200 °F