



**TRIVALENCE**

# TriLON™ 661BG35FR0 (U,L,HS,N)

**Polyamide Nylon 66**

## General Information

### Product Description

General purpose, 35% Glass Fiber Reinforced Nylon 66 Flame Retardant

#### FEATURES

- Great Strength
- Oil/Solvent Resistant
- Fast Cyling
- High Rigidity
- Excellent Chemical Resistance
- Gasoline Resistant
- 35% Glass Fiber Reinforced
- Flame Retardant

#### ADDITIONAL FORMULAS

- Added Lubricant "L"
- Additional UV "U"
- Additonal Heat Stabilizers "HS"
- Nucleated "N"

#### COLOR

- All
- Translucent/Opaque

### General

- |                             |   |
|-----------------------------|---|
| <b>Typical Applications</b> | -Appliance, automotive, general, pumps, impellers, housings |
| <b>Processing Method</b>    | -Injection  |
| <b>Form(s)</b>              | -Pellets  |
| <b>Compliance</b>           | -RoHS Compliant - TVT                                       |
| <b>Availability</b>         | -North America, Europe, Latin America                       |

## ASTM / ISO Properties<sup>1</sup>

Physical	Nominal Value Unit	Test Method
Density	1.47 g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.5 %	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass	TVT Internal
Mechanical	Nominal Value Unit	Test Method
Tensile Strength, brk	170 MPa	ISO 527
Tensile Strain,brk	>2 %	ISO 527
Flexural Modulus	10000 MPa	ISO 178
Charpy Notched Impact	10.0 kJ/m <sup>2</sup>	ISO 179
Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	255 °C	ISO 75
Deflection Temperature Under Load (1.8 MPa)	250 °C	ISO 75
Melting Point	260 °C	TVT Internal
Flammability	Nominal Value Unit	Test Method
1.5 mm	V0	UL94 - TVT Internal

### Recommended Processing Guidance

- |                             |               |
|-----------------------------|---------------|
| Drying Temperature          | 170 to 220 °F |
| Drying Time - DESSICANT     | 3 to 6 Hours  |
| Suggested Max Moisture      | 0.2 %         |
| Processing Melt Temperature | 540 to 570 °F |
| Mold Temperature            | 140 to 200 °F |