



**TRIVALENCE**

# TriLON™ 661BG35HS (U,L,HS,N) ISO

**Polyamide Nylon 66**

**General Information**

**Product Description**

35% Glass Fiber Reinforced Nylon 66 offered with various additives. High Strength

**FEATURES**

- Good Toughness
- Fast Cyling
- High Strength
- Gasoline Resistant
- 35% Glass Fiber Reinforced
- Oil/Solvent Resistant
- High Heat Resistance
- Excellent Chemical Resistance

**ADDITIONAL FORMULAS**

- Added Lubricant "L"
- Additional UV "U"
- Additional Heat Stabilizers "HS"
- Nucleated "N"

**COLOR**

- All
- Translucent/Opaque

**General**

- Typical Applications** -Appliance, transportation, pumps, impellers, housings, gears
- Processing Method** -Injection
- Form(s)** -Pellets
- Compliance** -RoHS Compliant - TVT
- Availability** -North America, Europe, Latin America

**ASTM / ISO Properties<sup>1</sup>**

	<b>Nominal Value Unit</b>	<b>Test Method</b>
<b>Physical</b>		
Density	1.40 g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.6 %	ISO 294
Molding Shrinkage - x- Flow (3.2mm)	1.0 to 1.4 %	ISO 294
Outdoor Suitability (QUV) ("U" Grades)	Pass	TVT Internal
<b>Mechanical</b>		
Tensile Strength, yld	195 MPa	ISO 527
Tensile Strain	>2.5 %	ISO 527
Flexural Modulus	9800 MPa	ISO 178
Notched Izod Impact	14 kJ/m <sup>2</sup>	ISO 180
<b>Thermal</b>		
Deflection Temperature Under Load (1.8 MPa)	252 °C	ISO 75
Melting Temperature	262 °C	ISO 3146
<b>Flammability</b>		
0.06 in	HB	UL94 - TVT Internal

**Recommended Processing Guidance**

- Drying Temperature 70 to 90 °C
- Drying Time - DESSICANT 3 to 6 Hours
- Suggested Max Moisture 0.2 %
- Processing Melt Temperature 285 to 305 °C
- Mold Temperature 80 to 100 °C