



TRIVALENCE

TriLON™ 662BG35 (U,L,HS,N) ISO

Polyamide Nylon 66

General Information

Product Description

35% Glass Fiber Reinforced Nylon 66 offered with various additives. High Strength

FEATURES

- Good Toughness
- Fast Cyling
- High Strength
- Gasoline Resistant
- 35% Glass Fiber Reinforced
- Oil/Solvent Resistant
- High Heat Resistance
- Excellent Chemical Resistance

ADDITIONAL FORMULAS

- Added Lubricant "L"
- Additional UV "U"
- Additional Heat Stabilizers "HS"
- Nucleated "N"

COLOR

- All
- Translucent/Opaque

General

- Typical Applications** -Appliance, transportation, pumps, impellers, housings, gears
- Processing Method** -Injection
- Form(s)** -Pellets
- Compliance** -RoHS Compliant - TVT
- Availability** -North America, Europe, Latin America

ASTM / ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.6	%	ISO 294
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, yld	205	MPa	ISO 527
Tensile Strain	>2	%	ISO 527
Flexural Modulus	9400	MPa	ISO 178
Notched Izod Impact	14	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa)	250	°C	ISO 75
Melting Temperature	262	°C	ISO 3146
Flammability	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 - TVT Internal

Recommended Processing Guidance

- Drying Temperature 70 to 90 °C
- Drying Time - DESSICANT 3 to 6 Hours
- Suggested Max Moisture 0.2 %
- Processing Melt Temperature 285 to 305 °C
- Mold Temperature 80 to 100 °C