



**TRIVALENCE**

# TriLON™ 663MS2 (U,L,HS,N)

**Polyamide Nylon 66**

**General Information**

**Product Description**

General purpose, Nylon 66 Impact Modified

**FEATURES**

- Great Impact
- Fast Cyling
- Excellent Chemical Resistance
- Gasoline Resistant
- Oil/Solvent Resistant
- Molybdenum Disulfide

**ADDITIONAL FORMULAS**

- Added Lubricant "L"
- Additional UV "U"
- Additonal Heat Stabilizers "HS"
- Nucleated "N"

**COLOR**

- All
- Translucent/Opaque

**General**

- Typical Applications** -Appliance, automotive, general
- Processing Method** -Injection
- Form(s)** -Pellets
- Compliance** -RoHS Compliant - TVT
- Availability** -North America, Europe, Latin America

**ASTM / ISO Properties<sup>1</sup>**

<b>Physical</b>	<b>Nominal Value Unit</b>	<b>Test Method</b>
Density	1.12 g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.2mm)	1.2 to 1.6 %	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass	TVT Internal
<b>Mechanical</b>	<b>Nominal Value Unit</b>	<b>Test Method</b>
Tensile Strength, yld	10,500 psi	ASTM D638
Tensile Strain	>40 %	ASTM D638
Flexural Modulus	270,000 psi	ASTM D790
Notched Izod Impact	6.0 ft-lbs/in	ASTM D256
<b>Thermal</b>	<b>Nominal Value Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load (1.8 MPa)	180 °F	ASTM D648
Melting Point	504 °F	TVT Internal
<b>Flammability</b>	<b>Nominal Value Unit</b>	<b>Test Method</b>
0.06 in	HB	UL94 - TVT Internal

**Recommended Processing Guidance**

- Drying Temperature 150 to 175 °F
- Drying Time - DESSICANT 3 to 6 Hours
- Suggested Max Moisture 0.2 %
- Processing Melt Temperature 540 to 570 °F
- Mold Temperature 140 to 200 °F