



TRIVALENCE

TriVAN™ 21G10PS (U, R, UR)

Acrylonitrile Butadiene Styrene Glass Fiber Reinforced

General Information		
Product Description Acrylonitrile Butadiene Styrene 10% Glass Fiber Reinforced		
FEATURES -Good Strength -Low Flow -Good Stiffness	ADDITIONAL FORMULAS -Added Release "R" -Additional UV "U"	COLOR -All -Opaque

General	
Typical Applications	-Appliance, construction.
Processing Method	-Injection/Extrusion
Form(s)	-Pellets
Availability	-North America, Europe, Latin America

ASTM / ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ASTM D792
Melt Flow Rate (230°C/3.8kg)	4	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.3 to 0.5	%	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, yld	9,000	psi	ASTM D638
Tensile Elongation	>2.0	%	ASTM D638
Flexural Modulus	580000	psi	ASTM D790
Notched Izod Impact	0.9	ft-lbs/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	210	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	195	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 - TVT Internal

Recommended Processing Guidance	
Drying Temperature	175 to 200 °F
Drying Time	3 to 5 Hours
Suggested Max Moisture	0.04 %
Processing Melt Temperature	480 to 530 °F
Mold Temperature	110 to 175 °F