



**TRIVALENCE**

# TriVAN™ 21G30 (U, R, UR)

**Acrylonitrile Butadiene Styrene Glass Fiber Reinforced**

Product Description	General Information
---------------------	---------------------

Acrylonitrile Butadiene Styrene 30% Glass Fiber Reinforced

**FEATURES**

- Good Impact
- Low Flow
- Good Stiffness

**ADDITIONAL FORMULAS**

- Added Release "R"
- Additional UV "U"

**COLOR**

- All
- Opaque

**General**

- |                             |                                       |
|-----------------------------|---------------------------------------|
| <b>Typical Applications</b> | -Appliance, construction.             |
| <b>Processing Method</b>    | -Injection/Extrusion                  |
| <b>Form(s)</b>              | -Pellets                              |
| <b>Availability</b>         | -North America, Europe, Latin America |

ASTM / ISO Properties <sup>1</sup>			
------------------------------------	--	--	--

Physical	Nominal Value	Unit	Test Method
Density	1.26	g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (230°C/3.8kg)	2	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.1 to 0.3	%	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, yld	14000	psi	ASTM D638
Tensile Elongation	>1.5	%	ASTM D638
Flexural Modulus	1200000	psi	ASTM D790
Notched Izod Impact	1.2	ft-lbs/in	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	235	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	225	°F	ASTM D648
Vicat Softening Temperature	230	°F	ASTM D1525

Flammability	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 - TVT Internal

Recommended Processing Guidance		
---------------------------------	--	--

Drying Temperature	175 to 200	°F
Drying Time	3 to 5	Hours
Suggested Max Moisture	0.04	%
Processing Melt Temperature	480 to 530	°F
Mold Temperature	110 to 175	°F