



**TRIVALENCE**

# TriVAN™ 22H (U, R, UR)

Acrylonitrile Butadiene Styrene

## General Information

### Product Description

Medium flow, high impact, high heat grade ABS used for extrusion and blow molding applications

#### FEATURES

- High Impact
- Medium Flow
- High Heat

#### ADDITIONAL FORMULAS

- Added Release "R"
- Additional UV "U"

#### COLOR

- All
- Opaque

### General

<b>Typical Applications</b>	-Appliance, construction, sheet, transportation
<b>Processing Method</b>	-Injection/Extrusion
<b>Form(s)</b>	-Pellets
<b>Availability</b>	-North America, Europe, Latin America

## ASTM / ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (230°C/3.8kg)	4	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.5 to 0.7	%	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, yld	6400	psi	ASTM D638
Tensile Elongation	>25	%	ASTM D638
Flexural Modulus	315000	psi	ASTM D790
Notched Izod Impact	4.5	ft-lbs/in	ASTM D256
Rockwell Hardness	112	R-Scale	ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	210	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	186	°F	ASTM D648
Vicat Softening Temperature	220	°F	ASTM D1525
CLTE - Flow	4.5E-5	in/in/°F	ASTM E831
Flammability	Nominal Value	Unit	Test Method
0.06 in		HB	UL94 - TVT Internal

### Recommended Processing Guidance

Drying Temperature	175 to 200 °F
Drying Time	3 to 5 Hours
Suggested Max Moisture	0.04 %
Processing Melt Temperature	450 to 520 °F
Mold Temperature	110 to 175 °F