



**TRIVALENCE**

# TriVAN™ 32SU\_

Acrylonitrile Styrene Acrylate - ASA

## General Information

### Product Description

High flow, good impact grade ASA

#### FEATURES

- Good Impact
- High Flow
- Weatherable

#### ADDITIONAL FORMULAS

- Added Release "R"

#### COLOR

- All
- Opaque

### General

<b>Typical Applications</b>	-Appliance, construction, transportation
<b>Processing Method</b>	-Injection/Extrusion
<b>Form(s)</b>	-Pellets
<b>Availability</b>	-North America, Europe, Latin America

## ASTM / ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.06	g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (220°C/10.0kg)	24	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.5 to 0.7	%	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, yld	5500	psi	ASTM D638
Tensile Elongation	>30	%	ASTM D638
Flexural Modulus	250000	psi	ASTM D790
Notched Izod Impact	3	ft-lbs/in	ASTM D256
Rockwell Hardness	88	R-Scale	ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	210	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	180	°F	ASTM D648
Vicat Softening Temperature	210	°F	ASTM D1525
CLTE - Flow	4.7E-5	in/in/°F	ASTM E831
Flammability	Nominal Value	Unit	Test Method
0.06 in		HB	UL94 - TVT Internal

### Recommended Processing Guidance

Drying Temperature	160 to 180 °F
Drying Time	3 to 5 Hours
Suggested Max Moisture	0.02 %
Processing Melt Temperature	480 to 530 °F
Mold Temperature	110 to 175 °F