



**TRIVALENCE**

# TriVEX™ 11G10FR2 (U,R)

**Polycarbonate**

**General Information**

**Product Description**

Flame retardant, 10% glass reinforced polycarbonate.

**FEATURES**

- Flame Retardant
- High Impact
- UV Stabilized
- Low Flow

**ADDITIONAL FORMULAS**

- Added Release "R"
- Added UV "U"

**COLOR**

-All

**General**

- |                             |   |
|-----------------------------|---|
| <b>Typical Applications</b> | -Appliance, electrical, lawn & garden, automotive, electronic |
| <b>Processing Method</b>    | -Injection/Extrusion  |
| <b>Form(s)</b>              | -Pellets  |
| <b>Availability</b>         | -North America, Europe, Asia, Latin America                   |

**ASTM / ISO Properties<sup>1</sup>**

<b>Physical</b>	<b>Nominal Value Unit</b>	<b>Test Method</b>
Density	1.25 g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (300°C/1.2kg)	6 g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.4 %	TVT Internal
Outdoor Suitability (QUV) ("U" grades only)	Pass	TVT Internal
<b>Mechanical</b>	<b>Nominal Value Unit</b>	<b>Test Method</b>
Tensile Strength, yld	9400 psi	ASTM D638
Tensile Elongation	10 %	ASTM D638
Flexural Modulus	480000 psi	ASTM D790
Notched Izod Impact	2.5 ft-lbs/in	ASTM D256
Rockwell Hardness	122 R-Scale	ASTM D785
<b>Thermal</b>	<b>Nominal Value Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load (0.45 MPa)	292 °F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	284 °F	ASTM D648
Vicat Softening Temperature	308 °F	ASTM D1525
RTI Elec	176 °F	UL 746
RTI IMP	176 °F	UL 746
RTI Str	176 °F	UL 746
CLTE - Flow	1.8E-5 in/in/°F	ASTM E831
<b>Flammability</b>	<b>Nominal Value Unit</b>	<b>Test Method</b>
0.06 in	V2	UL94 TVT Internal
0.12 in	V0	UL94 TVT Internal
<b>Recommended Processing Guidance</b>		
Drying Temperature	230 to 250 °F	
Drying Time	3 to 6 Hours	
Suggested Max Moisture	0.02 %	
Processing Melt Temperature	580 to 615 °F	
Mold Temperature	175 to 230 °F	