



TRIVALENCE

TriVEX™ 21G20FR0 (20M)

Polycarbonate

General Information

Product Description

Flame retardant, 20% glass reinforced product is available in melt flow ranges of 6 - 20.

FEATURES

- Flame Retardant
- High Impact
- UV Stabilized
- High Flow

ADDITIONAL FORMULAS

- Added Release "R"
- Added UV "U"
- Additional Melt Flows

COLOR

-All

General

- | | |
|-----------------------------|---|
| Typical Applications | -Appliance, electrical, lawn & garden, automotive, electronic |
| Processing Method | -Injection |
| Form(s) | -Pellets |
| Availability | -North America, Europe, Asia, Latin America |

ASTM / ISO Properties¹

Physical	Nominal Value Unit	Test Method
Density	1.35 g/cm ³	ASTM D792
Melt Flow Rate (300°C/1.2kg)	20 g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.4 %	TVT Internal
Outdoor Suitability (QUV) ("U" grades)	Pass	TVT Internal QUV

Mechanical	Nominal Value Unit	Test Method
Tensile Strength, yld	13000 psi	ASTM D638
Tensile Elongation	2 %	ASTM D638
Flexural Modulus	780000 psi	ASTM D790
Notched Izod Impact	1.6 ft-lbs/in	ASTM D256
Rockwell Hardness	122 R-Scale	ASTM D785

Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	300 °F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	294 °F	ASTM D648

Flammability	Nominal Value Unit	Test Method
0.06 in	V0	UL94
0.12 in	V0, 5VA	UL94

Recommended Processing Guidance

- | | |
|-----------------------------|---------------|
| Drying Temperature | 230 to 250 °F |
| Drying Time | 3 to 6 Hours |
| Suggested Max Moisture | 0.02 % |
| Processing Melt Temperature | 580 to 615 °F |
| Mold Temperature | 175 to 230 °F |