



TRIVALENCE

TriVEX™ 21G30FR2 (6M)

Polycarbonate

General Information

Product Description

Flame resistant, 30% glass reinforced product is available in melt flow ranges of 6 - 20.

FEATURES

- Flame Resistant
- Great Impact
- UV Stabilized
- Low Flow

ADDITIONAL FORMULAS

- Added Release "R"
- Added UV "U"
- Additional Melt Flows

COLOR

-All

General

- | | |
|-----------------------------|---|
| Typical Applications | -Appliance, electrical, lawn & garden, automotive, electronic |
| Processing Method | -Injection/Extrusion |
| Form(s) | -Pellets |
| Availability | -North America, Europe, Asia, Latin America |

ASTM / ISO Properties¹

Physical	Nominal Value Unit	Test Method
Density	1.42 g/cm ³	ASTM D792
Melt Flow Rate (300°C/1.2kg)	6 g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.4 %	TVT Internal
Outdoor Suitability (QUV) ("U" grades)	Pass	TVT Internal QUV

Mechanical	Nominal Value Unit	Test Method
Tensile Strength, yld	17000 psi	ASTM D638
Tensile Elongation	2 %	ASTM D638
Flexural Modulus	1060000 psi	ASTM D790
Notched Izod Impact	1.6 ft-lbs/in	ASTM D256
Rockwell Hardness	122 R-Scale	ASTM D785

Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	305 °F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	298 °F	ASTM D648

Flammability	Nominal Value Unit	Test Method
0.06 in	V2	UL94
0.12 in	V0	UL94

Recommended Processing Guidance	
Drying Temperature	230 to 250 °F
Drying Time	3 to 6 Hours
Suggested Max Moisture	0.02 %
Processing Melt Temperature	580 to 615 °F
Mold Temperature	175 to 230 °F