



**TRIVALENCE**

# TriVEX™ 22FR0 (14M)

Polycarbonate

Product Description	General Information
---------------------	---------------------

UL certified flame resistant product is available in melt flow ranges of 8 - 24.

**FEATURES**

- Flame Resistant
- Great Impact
- UV Stabilized

**ADDITIONAL FORMULAS**

- Added Release
- Additional Melt Flows

**COLOR**

- All



**General**

- |                             |   |
|-----------------------------|---|
| <b>Typical Applications</b> | -Appliance, electrical, lawn & garden, automotive |
| <b>Processing Method</b>    | -Injection  |
| <b>Form(s)</b>              | -Pellets  |
| <b>Availability</b>         | -North America, Europe, Asia, Latin America       |

ASTM / ISO Properties <sup>1</sup>		
Physical	Nominal Value Unit	Test Method

Density	1.21 g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (300°C/1.2kg)	14 g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.5 to 0.7 %	TVT Internal
Outdoor Suitability (QUV)	f1	UL 746C Pending

Mechanical	Nominal Value Unit	Test Method
------------	--------------------	-------------

Tensile Strength, brk	9200 psi	ASTM D638
Tensile Elongation	>100 %	ASTM D638
Flexural Modulus	320000 psi	ASTM D790
Notched Izod Impact	12 ft-lbs/in	ASTM D256
Rockwell Hardness	118 R-Scale	ASTM D785

Thermal	Nominal Value Unit	Test Method
---------	--------------------	-------------

Deflection Temperature Under Load (0.45 MPa)	278 °F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	270 °F	ASTM D648
Vicat Softening Temperature	308 °F	ASTM D1525
RTI Elec	239 °F	UL 746B Pending
RTI IMP	239 °F	UL 746B Pending
RTI Str	239 °F	UL 746B Pending
CLTE - Flow	3.8E-5 in/in/°F	ASTM E831

Flammability	Nominal Value Unit	Test Method
--------------	--------------------	-------------

0.06 in	V0	UL94 File E494706
0.10 in	V0, 5VA	UL94 File E494706

Recommended Processing Guidance	Nominal Value Unit
---------------------------------	--------------------

Drying Temperature	230 to 250 °F
Drying Time	3 to 6 Hours
Suggested Max Moisture	0.02 %
Processing Melt Temperature	520 to 560 °F
Mold Temperature	140 to 180 °F