



**TRIVALENCE**

# TriVEX™ 22FR0f1 (18M)

**Polycarbonate**

Product Description	General Information
---------------------	---------------------

UL certified flame resistant product is available in melt flow ranges of 8 - 24.

**FEATURES**

- Flame Resistant    -Weatherable (f1)
- Great Impact      -Elevated RTI
- UV Stabilized
- Higher Flow

**ADDITIONAL FORMULAS**

- Added Release
- Additional Melt Flows

**COLOR**

-All

**PENDING APPROVAL:**



**Underwriters Laboratories**

**General**

- |                             |   |
|-----------------------------|---|
| <b>Typical Applications</b> | -Appliance, electrical, lawn & garden, automotive |
| <b>Processing Method</b>    | -Injection  |
| <b>Form(s)</b>              | -Pellets  |
| <b>Availability</b>         | -North America, Europe, Asia, Latin America       |

ASTM / ISO Properties <sup>1</sup>		
------------------------------------	--	--

Physical	Nominal Value Unit	Test Method
Density	1.21 g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (300°C/1.2kg)	18 g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.5 to 0.7 %	TVT Internal
Outdoor Suitability (UV)	f1	UL 746C

Mechanical	Nominal Value Unit	Test Method
Tensile Strength, brk	9200 psi	ASTM D638
Tensile Elongation	>100 %	ASTM D638
Flexural Modulus	320000 psi	ASTM D790
Notched Izod Impact	12 ft-lbs/in	ASTM D256
Rockwell Hardness	118 R-Scale	ASTM D785

Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	278 °F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	270 °F	ASTM D648
Vicat Softening Temperature	308 °F	ASTM D1525
RTI Elec	266 °F	UL 746B
RTI IMP	257 °F	UL 746B
RTI Str	257 °F	UL 746B
CLTE - Flow	3.8E-5 in/in/°F	ASTM E831

Flammability	Nominal Value Unit	Test Method
0.06 in	V0	UL94 File E494706
0.10 in	V0, 5VA	UL94 File E494706

Recommended Processing Guidance	
---------------------------------	--

- |                             |               |
|-----------------------------|---------------|
| Drying Temperature          | 230 to 250 °F |
| Drying Time                 | 3 to 6 Hours  |
| Suggested Max Moisture      | 0.02 %        |
| Processing Melt Temperature | 520 to 560 °F |
| Mold Temperature            | 140 to 180 °F |