



TRIVALENCE

TriVEX™ 23FR5 (10M), E494706 UL Pending

Polycarbonate

General Information

Product Description

UL certified flame resistant product is available in melt flow ranges of 8 - 24.

FEATURES

- Flame Resistant -Elevated RTI
- Great Impact
- UV Stabilized
- f1

ADDITIONAL FORMULAS

- Added Release
- Additional Melt Flows

COLOR

-All



Underwriters Laboratories

General

- Typical Applications** -Appliance, electrical, lawn & garden, automotive
- Processing Method** -Injection
- Form(s)** -Pellets
- Availability** -North America, Europe, Asia, Latin America

ASTM / ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm ³	ASTM D792
Melt Flow Rate (300°C/1.2kg)	10	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.5 to 0.7	%	TVT Internal
Outdoor Suitability (QUV)	f1		UL 746C Pending

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, brk	9200	psi	ASTM D638
Tensile Elongation	>100	%	ASTM D638
Flexural Modulus	320000	psi	ASTM D790
Notched Izod Impact	12	ft-lbs/in	ASTM D256
Rockwell Hardness	118	R-Scale	ASTM D785

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	278	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	270	°F	ASTM D648
Vicat Softening Temperature	308	°F	ASTM D1525
RTI Elec	239	°F	UL 746B Pending
RTI IMP	239	°F	UL 746B Pending
RTI Str	239	°F	UL 746B Pending
CLTE - Flow	3.8E-5	in/in/°F	ASTM E831

Flammability	Nominal Value	Unit	Test Method
0.06 in	V0		UL94 File E494706
0.10 in	V0, 5VA		UL94 File E494706

Recommended Processing Guidance	Nominal Value	Unit
Drying Temperature	230 to 250	°F
Drying Time	3 to 6	Hours
Suggested Max Moisture	0.02	%
Processing Melt Temperature	520 to 560	°F
Mold Temperature	140 to 180	°F