



TRIVALENCE

TriVEX™ 23IM (U,R)

Polycarbonate

General Information

Product Description

General purpose, high flow, high impact polycarbonate

FEATURES

- Great Impact
- Good Flow

ADDITIONAL FORMULAS

- Added Release "R"
- Additional UV "U"

COLOR

- All
- Opagues

General

- | | |
|-----------------------------|--|
| Typical Applications | -Appliance, electrical, lawn & garden, automotive, medical |
| Processing Method | -Injection |
| Form(s) | -Pellets |
| Availability | -North America, Europe, Asia, Latin America |

ASTM / ISO Properties¹

Physical	Nominal Value Unit	Test Method
Density	1.20 g/cm ³	ASTM D792
Melt Flow Rate (300°C/1.2kg)	20 g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.5 to 0.7 %	TVT Internal
Outdoor Suitability (QUV) (12U Grades)	Pass	TVT Internal

Mechanical	Nominal Value Unit	Test Method
Tensile Strength, brk	9500 psi	ASTM D638
Tensile Elongation	>120 %	ASTM D638
Flexural Modulus	325000 psi	ASTM D790
Notched Izod Impact	15 ft-lbs/in	ASTM D256
Rockwell Hardness	118 R-Scale	ASTM D785

Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	278 °F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	270 °F	ASTM D648
Vicat Softening Temperature	308 °F	ASTM D1525
CLTE - Flow	3.8E-5 in/in/°F	ASTM E831

Flammability	Nominal Value Unit	Test Method
0.06 in	HB	UL94 - TVT Internal

Recommended Processing Guidance

- | | |
|-----------------------------|---------------|
| Drying Temperature | 230 to 250 °F |
| Drying Time | 3 to 6 Hours |
| Suggested Max Moisture | 0.02 % |
| Processing Melt Temperature | 520 to 560 °F |
| Mold Temperature | 140 to 180 °F |