



**TRIVALENCE**

# TriVEX™ 32G10 (U,R)

**Polycarbonate**

General Information
---------------------

Product Description
---------------------

Glass fiber reinforced polycarbonate

**FEATURES**

- 10% Glass Fiber Reinforced
- Great Strength
- Good Creep Resistance
- High Flow

**ADDITIONAL FORMULAS**

- Added Release "R"
- Added UV "U"

**COLOR**

-All

General
---------

- |                             |   |
|-----------------------------|---|
| <b>Typical Applications</b> | -Appliance, electrical, lawn & garden, automotive, electronic |
| <b>Processing Method</b>    | -Injection  |
| <b>Form(s)</b>              | -Pellets  |
| <b>Availability</b>         | -North America, Europe, Asia, Latin America                   |

ASTM / ISO Properties <sup>1</sup>
------------------------------------

Physical	Nominal Value	Unit	Test Method
----------	---------------	------	-------------

Density	1.26	g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (300°C/1.2kg)	20	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.5	%	TVT Internal
Outdoor Suitability - QUV ("U" grades only)	Pass		QUV - TVT Internal

Mechanical	Nominal Value	Unit	Test Method
------------	---------------	------	-------------

Tensile Strength, yld	10500	psi	ASTM D638
Tensile Elongation	10	%	ASTM D638
Flexural Modulus	505,000	psi	ASTM D790
Notched Izod Impact	2.2	ft-lbs/in	ASTM D256
Rockwell Hardness	122	R-Scale	ASTM D785

Thermal	Nominal Value	Unit	Test Method
---------	---------------	------	-------------

Deflection Temperature Under Load (0.45 MPa)	295	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	278	°F	ASTM D648
Vicat Softening Temperature	302	°F	ASTM D1525
CLTE - Flow	1.8E-5	in/in/°F	ASTM E831

Flammability	Nominal Value	Unit	Test Method
--------------	---------------	------	-------------

0.06 in	HB		UL94 TVT Internal
---------	----	--	-------------------

Recommended Processing Guidance
---------------------------------

Drying Temperature	230 to 250	°F	
Drying Time	3 to 6	Hours	
Suggested Max Moisture	0.02	%	
Processing Melt Temperature	590 to 640	°F	
Mold Temperature	175 to 230	°F	