



TRIVALENCE

TriVOL 21C40 (U,R)

Polypropylene

General Information			
---------------------	--	--	--

Product Description			
---------------------	--	--	--

Homopolymer PP, calcium carbonate reinforced. melt flow ranges (13-24)

FEATURES

-RoHS/REACH Compliant
-Homopolymer
-40% Calcium Carbonate Reinforced

ADDITIONAL FORMULAS

-Added Release "R"
-Added UV "U"

COLOR

-All

General	
---------	--

Typical Applications -Appliance, electrical, lawn & garden, automotive, packaging, industrial

Processing Method -Injection

Form(s) -Pellets

Availability -North America, Europe, Asia, Latin America

ASTM / ISO Properties ¹			
------------------------------------	--	--	--

Physical	Nominal Value	Unit	Test Method
----------	---------------	------	-------------

Density	1.21	g/cm ³	ASTM D792
Melt Flow Rate (230°C/2.16kg)	18	g/10min	ASTM D1238
Outdoor Suitability (QUV) ("U" grades)	Pass		TVT Internal

Mechanical	Nominal Value	Unit	Test Method
------------	---------------	------	-------------

Tensile Strength	5,000	psi	ASTM D638
Tensile Elongation	>8	%	ASTM D638
Flexural Modulus	450,000	psi	ASTM D790
Notched Izod Impact	0.8	ft-lbs/in	ASTM D256

Thermal	Nominal Value	Unit	Test Method
---------	---------------	------	-------------

Deflection Temperature Under Load (0.45 MPa)	265	°F	ASTM D648
--	-----	----	-----------

Flammability	Nominal Value	Unit	Test Method
--------------	---------------	------	-------------

0.06 in	HB		UL94 File E494706
---------	----	--	-------------------

Recommended Processing Guidance	Nominal Value	Unit
---------------------------------	---------------	------

Drying Temperature	160 to 200	°F
Drying Time	1 to 3	Hours
Suggested Max Moisture	0.05	%
Processing Melt Temperature	410 to 480	°F
Mold Temperature	80 to 140	°F