



TRIVALENCE

TriVOL 22T10 (U,R)

Polypropylene

General Information

Product Description

Copolymer PP, talc reinforced. melt flow ranges (13-24)

FEATURES

- RoHS/REACH Compliant
- Copolymer
- 10% Talc Reinforced

ADDITIONAL FORMULAS

- Added Release "R"
- Added UV "U"

COLOR

-All

General

- Typical Applications** -Appliance, electrical, lawn & garden, automotive, packaging, industrial
- Processing Method** -Injection
- Form(s)** -Pellets
- Availability** -North America, Europe, Asia, Latin America

ASTM / ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density	0.97	g/cm ³	ASTM D792
Melt Flow Rate (230°C/2.16kg)	18	g/10min	ASTM D1238
Outdoor Suitability (QUV) ("U" grades)	Pass		TVT Internal
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	3,200	psi	ASTM D638
Tensile Elongation	>15	%	ASTM D638
Flexural Modulus	165,000	psi	ASTM D790
Notched Izod Impact	1.8	ft-lbs/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	210	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 File E494706
Recommended Processing Guidance	Nominal Value	Unit	
Drying Temperature	160 to 200	°F	
Drying Time	1 to 3	Hours	
Suggested Max Moisture	0.05	%	
Processing Melt Temperature	410 to 480	°F	
Mold Temperature	80 to 140	°F	