



**TRIVALENCE**

# TriVOL 32 (U,R,N)

**Polypropylene Copolymer**

Product Description	General Information
---------------------	---------------------

General purpose, impact modified, copolymer PP.

**FEATURES**

- Impact Copolymer
- Cold Temperature Ductility
- High Flow

**ADDITIONAL FORMULAS**

- Added Release "R"
- Additional UV "U"
- Nucleated "N"

**COLOR**

- All
- Opaque

**General**

- |                             |   |
|-----------------------------|---|
| <b>Typical Applications</b> | -Automotive, sporting goods, packaging, consumer goods. |
| <b>Processing Method</b>    | -Injection  |
| <b>Form(s)</b>              | -Pellets  |
| <b>Availability</b>         | -North America, Europe, Asia                            |

ASTM / ISO Properties <sup>1</sup>			
------------------------------------	--	--	--

Physical	Nominal Value	Unit	Test Method
Density	0.92	g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (230°C/2.16kg)	20	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	1.2 to 1.5	%	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, yld	3700	psi	ASTM D638
Tensile Elongation, brk	>200	%	ASTM D638
Flexural Modulus	160000	psi	ASTM D790
Notched Izod Impact	1.8	ft-lbs/in	ASTM D256
Hardness, Shore D	80	D-Scale	ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	190	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 - TVT Internal

Recommended Processing Guidance	
---------------------------------	--

- |                             |               |
|-----------------------------|---------------|
| Drying Temperature          | 150 to 175 °F |
| Drying Time                 | 2 to 4 Hours  |
| Suggested Max Moisture      | 0.02 %        |
| Processing Melt Temperature | 410 to 470 °F |
| Mold Temperature            | 80 to 140 °F  |