



GRADE: RE-NY66-0135GHY BLACK

Molding Grade PA 66 heat stabilized w/ 35% hydrolytically stabilized glass reinforcement & 25% Pre-consumer Validated Recycled Content Materials

Typical Material Properties

Physical	Nominal Values	ASTM Test
Specific Gravity	1.40	D792
Mechanical		
Tensile Strength	24,500 psi	D638
Flexural Modulus	1,700,000 psi	D790
Flexural Strength @ Yield	34,500 psi	D790
Elongation @ Break	2.3 %	D638
Impact		
Izod Impact (73 °F, 0.125)	12.5 ft-lb/in	D256
Thermal		
Melting Temperature	500 °F	D3418
Heat Deflection Temp @ 264 psi	480 °F	D638

Recommended Processing Guidelines

	Nominal Values
Drying Time and Temperature	2-6 hrs at 176-185°F
Suggested Max Moisture	<0.20%
Rear Temperature	428 – 464 °F
Middle Temperature	464 – 491 °F
Front Temperature	464 – 500 °F
Nozzle Temperature	464 – 491 °F
Processing (Melt) Temperature	440 – 530 °F
Mold Temperature	150 – 250 °F