



**Grade: re-PCR-FR1004 (f1)**

Molding Grade PC FR w/ UV and Release, All Colors  
100% Validated Pre-consumer Recycled Content

**Typical Material Properties**

Physical	Nominal Values	ASTM Test
Specific Gravity	1.20	D792
Melt Flow (300°C/1.2kg)	19.0 g/10 min	D1238
<b>Mechanical</b>		
Tensile Modulus	340,000 psi	D638
Tensile Strength @ Yield	9,000 psi	D638
Flexural Modulus	350,000 psi	D790
Flexural Strength @ Yield	14,000 psi	D790
<b>Impact</b>		
Notched Izod Impact (73 °F, 0.125 in)	14.0 ft-lb/in	D256
<b>Thermal</b>		
DTUL @ 264 psi-unannealed (0.125 in)	260 °F	D648
<b>Mold Shrinkage</b>		
Linear Flow	.004 - .007 in/in	D955
<b>UL Rating</b>		
Flammability RTI	V-2 @ 1.5mm, V-2 @ 3mm 125°C, 115°C, 125°C	UL 94 UL746B

**Recommended Processing Guidelines**

	Nominal Values
Drying Time and Temperature	4.0 hrs, 250°F
Suggested Max Moisture	0.020%
Rear Temperature	520°F – 550 °F
Middle Temperature	530°F – 570 °F
Front Temperature	550°F – 600 °F
Nozzle Temperature	550°F – 600 °F
Processing (Melt) Temperature	550°F – 600 °F
Mold Temperature	170°F – 220 °F
Back Pressure	50 – 100 psi
Screw Speed	40 – 75 RPM