



A subsidiary of ICC Industries Inc.



# PRIME COR-X PP WITH VANISH

Copolymer Polypropylene

Primex Corporation, along with our subsidiaries, are committed to sustainable practices that are ethical, responsible, and create value for customers, employees, and future generations.

REDUCE • REUSE • RECYCLE • REPLACE

## Technical Data Sheet

Property	Test Method	Value	Unit
Specific Gravity	D-1505	.906	g/cc
Melt Flow	D-1238	.5	g/10min
Tensile Strength @ Yield	D-638	4,000	psi
Elongation @ Break	D-638	>500	%
Flexural Modulus	D-790	195,000	psi
Heat Deflection Temp @ 66 psi	D-648	190	°F
Impact Strength, notched Izod 1/8" notch @ 73°F	D-256	No Break	ft-lb/in
Hardness	D-785	75	Rockwell R

UL 94HB  
Complies with FDA Regulation 21 CFR 177.1520

