



A subsidiary of ICC Industries Inc.



PRIME BIOGREEN 650

Biodegradable/ Compostable Material

Primex Corporation, along with our subsidiaries, are committed to sustainable practices that are ethical, responsible, and create value for customers, employees, and future generations.

REDUCE • REUSE • RECYCLE • REPLACE

Technical Data Sheet

Property	Test Method	Value	Unit
Specific Gravity	D-792	1.25	g/cc
Melt Flow @ 190°C/5kg	D-1238	36.5	g/10min
Tensile Strength @ Yield	D-638	7,400	psi
Tensile Strength @ Break	D-638	4,500	psi
Elongation @ Break	D-638	9	%
Heat Deflection Temp @66 psi, unannealed	D-648	127	°F
Vicat Softening Point	D-1525	146	°F

FDA status to be determined.
Flammability to be determined.

