

K0017  
Europe

## KRATON® D1192 A Polymer

Data Document

Identifier : K017DDg11E

## Description

Kraton D1192 A is a clear linear block copolymer based on styrene and butadiene with bound styrene of 30% mass. It is supplied from Europe in the physical forms described below:

- Kraton D1192 AT - supplied as porous pellets dusted with talc
- Kraton D1192 AS - supplied as porous pellets dusted with amorphous silica
- Kraton D1192 ASM - supplied as powder dusted with amorphous silica
- Kraton D1192 ATM - supplied as powder dusted with talc for the North American market

Kraton D1192 A is used for modification of industrial and paving bitumen. It may also be suitable for use in formulating adhesives, sealants and coatings, and in the modification of polymers.

## Sales Specifications

Property	Test Method	Units	Sales Specification Range	Notes
Apparent Molecular Mass of Triblock	KM 01	kg/mol	138 TO 162	
Polystyrene Content	KM 03	%m	28.5 TO 32.5	
Vinyl Content	KM 03	%	$\gamma = 35$	
Triblock Content	KM 01	%	$\gamma = 90$	
Total Extractables	KM 05	%m	$\alpha = 1.0$	
Volatile Matter	KM 04	%m	$\alpha = 0.3$	
Antioxidant Content	KM 08	%m	$\gamma = 0.16$	
Ash (AS, AT)	ISO 247	%m	0.1 TO 0.4	
Ash (ATM)	BAM 908	%w	4.0 TO 6.0	
Ash (ASM)	ISO 247	%m	2.5 TO 5.0	

## Typical Properties (These are typical values and may not routinely be measured on finished product)

Property	Test Method	Units	Typical Value	Notes
Bulk Density	ASTM D 1895 method B	kg/dm <sup>3</sup>	0.4	
Specific Gravity	ISO 2781		0.94	
Hardness, Shore A (15 sec)	ASTM D 2240	Hardness, Shore A (15 sec)	70	a
Melt Flow Rate, 200°C/5kg	ISO 1133	g/10min.	< 1	

**a** Measured on compression molded slabs

## Packaging

Kraton Polymers are available in a number of different package types. For information specific to this grade, please contact your local Kraton Polymers representative.

(R) KRATON and the KRATON logo are trademarks owned by the KRATON Polymers Group of Companies