**Technical Data Sheet**

# BADAMID® | UL B70 GF35

PA6-GF35

Polyamide 6 injection moulding grade with 35% of glass fibre reinforcement, UL-Listed

| Properties | Test conditions | Test method | Unit | dry as molded | conditioned 23 ° C, 50 % r.F. |
|---|---|---|---|---|---|
| **Mechanical Properties** | | | | | |
| Tensile Modulus | 23°C, 1 mm/Min | ISO 527-1/2 | MPa | 10800 | 7300 |
| Tensile Strength at yield | 23°C, 50 mm/Min | ISO 527-1/2 | MPa | - | - |
| Tensile strain at yield | 23°C, 50 mm/Min | ISO 527-1/2 | % | - | - |
| Nominal strain at break | 23°C, 50 mm/Min | ISO 527-1/2 | % | - | - |
| Tensile stress at break | 23°C, 5 mm/Min | ISO 527-1/2 | MPa | 190 | 125 |
| Tensile strain at break | 23°C, 5 mm/Min | ISO 527-1/2 | % | 3.5 | 5.5 |
| Flexural Modulus | 23°C | ISO 178 | MPa | - | - |
| Flexural Strength | 23°C | ISO 178 | MPa | 280 | 210 |
| Charpy Impact Strength | 23°C<br>-30°C | ISO 179/1eU<br>ISO 179/1eU | kJ/m²<br>kJ/m² | 95<br>90 | 110 |
| Charpy Notched Impact Strength | 23°C<br>-30°C | ISO 179/1eA<br>ISO 179/1eA | kJ/m²<br>kJ/m² | 17<br>15 | 26 |
| Izod Notched Impact Strength | 23°C<br>-30°C | ISO 180/1A<br>ISO 180/1A | kJ/m²<br>kJ/m² | 16<br>12 | 21 |
| Ball indentation hardness | 358 N | ISO 2039-1 | MPa | - | - |
| **Thermal Properties** | | | | | |
| Melting temperature | 10 K/min | ISO 3146 | °C | 222 | |
| Temperature of deflection under load | 0,45 MPa<br>1,8 MPa<br>8 MPa | ISO 75-1/2<br>ISO 75-1/2<br>ISO 75-1/2 | °C<br>°C<br>°C | 220<br>215<br>- | |
| Coefficient of linear thermal expansion | parallel<br>across | ISO 11359-2<br>ISO 11359-2 | E-4/K<br>E-4/K | 0.17<br>0.64 | |
| Thermal conductivity | Test plate 2 mm | DIN 52612-1 | W/(m*K) | - | |
| Maximum service temperature (50% decrease in tensile strength) | some hours<br>20.000 h | IEC-60216<br>IEC-60216 | °C<br>°C | 200<br>110 | |
| Flammability | | UL94<br>UL94<br>UL94<br>UL94 | Wall thickness mm<br>Rating<br>Wall thickness mm<br>Rating | 0.75<br>HB<br>1.5<br>HB | |
| Glow wire test GWIT | | IEC-60695-2-13<br>IEC-60695-2-13<br>IEC-60695-2-13<br>IEC-60695-2-13 | Wall thickness mm<br>Temperature °C<br>Wall thickness mm<br>Temperature °C | -<br>-<br>-<br>- | |
| Glow wire test GWFI | | IEC-60695-2-12<br>IEC-60695-2-12<br>IEC-60695-2-12<br>IEC-60695-2-12 | Wall thickness mm<br>Temperature °C<br>Wall thickness mm<br>Temperature °C | -<br>-<br>-<br>- | |
| **Electrical Properties** | | | | | |
| Relative Permittivity | 1 MHz | IEC-62631-2-1 | - | 3.9 | 6.4 |
| Dissipation Factor | 1 MHz | IEC-62631-2-1 | E-4 | 210 | 1900 |
| Spec. Volume Resistivity | - | IEC-62631-3-1 | Ohm*cm | 1.0E15 | 1.0E12 |

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168

**Technical Data Sheet**

# BADAMID® | UL B70 GF35

PA6-GF35

Polyamide 6 injection moulding grade with 35% of glass fibre reinforcement, UL-Listed

| Properties | Test conditions | Test method | Unit | dry as molded | conditioned 23 ° C, 50 % r.F. |
|---|---|---|---|---|---|
| Spec. Surface Resistivity | - | IEC-62631-3-2 | Ohm | 1.0E12 | 1.0E10 |
| Dielectric Strength | - | IEC-60243-1 | kV/mm | - | - |
| Comparative Tracking Index (CTI) | - | IEC-60112 | V | 500 | - |
| **Other Data** | | | | | |
| Water absorption | 23°C, Saturation | ISO 62 | % | 6.2 | |
| Moisture absorption | 23°C, 50% r.h. | ISO 62 | % | 2.0 | |
| Density | 23°C | ISO 1183 | g/cm³ | 1.41 | |
| Melt Volume Rate (MVR)<br><br><br> | Value<br>Temperature<br>Test Load | ISO 1133<br>ISO 1133<br>ISO 1133 | cm³/10min<br>°C<br>kg | -<br>-<br>- | |
| Viscosity number | 0,5% in 96% H2SO4 | ISO 307 | cm³/g | - | |
| **Processing injection molding** | | | | | |
| Melt temperature | | | °C | 270 - 300 | |
| Mold temperature | | | °C | 80 - 90 | |
| Guide Value Moisture | | | % | < 0.15 | |
| Drying temperature | | | °C | 80 | |
| Guide Value Drying time | | | h | 2 - 4 | |

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168