Technical Data Sheet

Badadur® PBT/PC 18 FR V0

PBT-PC 18 FR
Medium viscosity, flame retardent injection moulding grade with a well balanced ratio between mechanic and processing properties

Properties	Test Conditions	Test Methods	Units	Typical Values
Mechanical Properties				
Tensile Modulus [1]	23° C, 1 mm/Min	ISO 527-1/2	MPa	2600
Yield Stress [1]	23° C, 50 mm/Min	ISO 527-1/2	MPa	*
Yield Strain [1]	23° C, 50 mm/Min	ISO 527-1/2	%	*
Nominal Stress at Break [1]	23° C, 50 mm/Min	ISO 527-1/2	%	4
Stress at Break [1]	23° C, 5 mm/Min	ISO 527-1/2	MPa	57
Strain at Break [1]	23° C, 5 mm/Min	ISO 527-1/2	%	9
Bending Strength [2]	23° C	ISO 178	MPa	-
Charpy Impact Strength, unnotched [2]	23° C -30° C	ISO 179/1eU ISO 179/1eU	kJ/m2 kJ/m2	KB KB
Notched Charpy Impact Strength [2]	23° C -30° C	ISO 179/1eA ISO 179/1eA	kJ/m2 kJ/m2	17 14
Izod notched Impact Strength [2]	23° C -30° C	ISO 180/1A ISO 180/1A	kJ/m2 kJ/m2	- -
Thermal Properties				
Melting Temperature [3]	10 K/Min	ISO 3146	°C	223
Temperature of Deflection under Load [4]	0,45 MPa 1,8 MPa	ISO 75-1/2 ISO 75-1/2	°C °C	125 110
Coefficient of Linear Thermal Elongation [5]	parallel direction transverse direction	DIN 53752 DIN 53752	E-4/K E-4/K	0,9 1,0
Maximum Service Temperature	some hours 20 000 h 50 % Decrease in Tensile Strength or Yield Stress	- IEC 216	°C °C	130 110
Flammability [6]	0,8 mm 1,6 mm	UL 94 UL 94	Class Class	- V0
Glow Wire Test	0,75 mm / 1,6 mm 0,75 mm / 1,6 mm	GWIT GWFI	IEC-60695-2-13 IEC-60695-2-12	- 960
Electric Properties				
Relative Permittivity [7]	1 MHz	IEC 250	-	3,1
Dissipation Factor [7]	1 MHz	IEC 250	E-4	145
Specific Volume Resistivity [7]	-	IEC 93	Ohm cm	$>10^{17}$
Specific Surface Resistivity [7]	-	IEC 93	Ohm	$>10^{15}$
Dielectric Strength [7]	-	IEC 243-1	kV/mm	25
Comparative Tracking Index	-	IEC 112	V	600
Other data				
Water Absorption	23° C, Saturation	ISO 62	%	0,21
Moisture Absorption	23° C, 50 % r.H.	ISO 62	%	0,09
Melt Volume Rate (MVR)	250° C/2,16kg	ISO 1133	cm^3/10 min	-
Density	23° C	ISO 1183	g/ccm	1,32
Processing				
Melt Temperature	-	-	°C	240 – 260
Tool Surface Temperature	-	-	°C	60 – 100
Drying Temperature	-	-	°C	110 - 130
Drying Time	-	-	h	2 – 4h

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168