Technical data sheet

Badaprene® TPV 55A 1041

PP/EPDM - Compound

For injection moulding and extrusion, suitable for car glass encapsulation

Properties	Norm	Unit	Result
Hardness	DIN 53505	Shore A Shore D	56A -
Density	DIN 53505	g/cm^3	0,91
Tensil strength Parallel Normal	DIN 53505	MPa	 4,8 -
Strain at break Parallel Normal	DIN 53505	%	 470 -
Tear strength Parallel Normal	DIN 53505	N/mm	 18 -
Compression set 72h/23° C 24h/70° C 24h/100° C	DIN 53505	%	 - 36 -

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168