

Technical Data Sheet

Accucomp ACE092L

Acetal (POM) Copolymer
LyondellBasell Industries
Engineering Plastics

General			
Features	• Medium Viscosity		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.41	1.41 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 Kg)	9.0 g/10 min	9.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	8990 psi	62.0 MPa	ASTM D638
Tensile Elongation (Break)	60 %	60 %	ASTM D638
Flexural Modulus	384000 psi	2650 MPa	ASTM D790
Flexural Strength	13300 psi	92.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	1.2 ft·lb/in	65 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	80	80	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	316 °F	158 °C	
264 Psi (1.8 Mpa), Unannealed	230 °F	110 °C	
Melting Temperature	329 °F	165 °C	

Notes

These are typical property values not to be construed as specification limits.