

Technical Data Sheet

Hifax TRC 2185P C13055



Polypropylene Compounds

Product Description

Hifax TRC 2185P C13055 is a 12% talc filled PP copolymer, with high flowability and high impact resistance. Product is available as a customized color matched, pellet form. This grade is delivered in C13055 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

| | |
|--------------------------|--|
| Application | Exterior Trim |
| Market | Automotive |
| Processing Method | Injection Molding |
| Attribute | Good Color Stability; Good Processability; Good UV Resistance; High Flow; High Impact Resistance |

| Typical Properties | Nominal Value | Units | Test Method |
|---|---------------|-------------------|---------------|
| Physical | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 22 | g/10 min | ISO 1133-1 |
| Density, (23 °C) | 0.99 | g/cm ³ | ISO 1183-1/A |
| Mechanical | | | |
| Flexural Modulus, (23 °C, Tech. A) | 1600 | MPa | ISO 178/A1 |
| Impact | | | |
| Notched Izod Impact Strength | | | |
| (23 °C) | 45 | kJ/m ² | ISO 180/1A |
| (-30 °C) | 5.5 | kJ/m ² | ISO 180/1A |
| Thermal | | | |
| Deflection Temperature Under Load, (0.45 MPa, Unannealed) | 90 | °C | ISO 75B-1, -2 |