

Technical Data Sheet

Fiberfil® PP-60/TC/40/OP WT2595

Polypropylene Homopolymer
Engineering Plastics



General			
Filler / Reinforcement	• Talc, 40% Filler by Weight		
Features	• Homopolymer		
Appearance	• White		
Forms	• Pellets		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.30	1.30 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Molding Shrinkage - Flow			ASTM D955
0.125 in (3.18 mm)	5.0E-3 to 6.0E-3 in/in	0.50 to 0.60 %	
0.250 in (6.35 mm)	6.0E-3 to 7.0E-3 in/in	0.60 to 0.70 %	
Water Absorption (24 hr)	0.030 %	0.030 %	ASTM D570

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus (73°F (23°C))	750000 psi	5170 MPa	ASTM D638
Tensile Strength (73°F (23°C))	4300 psi	29.6 MPa	ASTM D638
Tensile Elongation (Yield, 73°F (23°C))	15 %	15 %	ASTM D638
Flexural Modulus - Tangent (73°F (23°C))	610000 psi	4210 MPa	ASTM D790
Flexural Strength (73°F (23°C))	8800 psi	60.7 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 in (3.18 mm)	0.50 ft·lb/in	27 J/m	

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-Scale)	90 to 100	90 to 100	ASTM D785


Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	290 °F	143 °C	
264 psi (1.8 MPa), Unannealed	220 °F	104 °C	

Technical Data Sheet

**Fiberfil® PP-60/TC/40/OP
WT2595**

Polypropylene Homopolymer
Engineering Plastics

lyondellbasell



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	170 °F	77 °C
Drying Time	2.0 hr	2.0 hr
Suggested Max Moisture	0.20 %	0.20 %
Rear Temperature	390 to 410 °F	199 to 210 °C
Middle Temperature	400 to 440 °F	204 to 227 °C
Front Temperature	360 to 390 °F	182 to 199 °C
Nozzle Temperature	360 to 380 °F	182 to 193 °C
Processing (Melt) Temp	390 to 450 °F	199 to 232 °C
Mold Temperature	90 to 160 °F	32 to 71 °C
Injection Rate	Moderate-Fast	Moderate-Fast
Back Pressure	0.00 to 100 psi	0.00 to 0.689 MPa

Injection Notes

Screw speed: Medium to Fast

Notes

These are typical property values not to be construed as specification limits.