

Technical Data Sheet

Hostacom FPP 40T LE K2274

Polypropylene Homopolymer

LyondellBasell Industries

Engineering Plastics

Product Description

40% talc-filled PP-Homopolymercompound, low emission and low odour.

Former name: Polyfort FPP 40T LE K2274

General

Filler / Reinforcement	• Talc, 40% Filler by Weight
Features	• Homopolymer
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PP-H 40T LE

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.25 g/cm ³	1.25 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 Kg)	8.0 cm ³ /10min	8.0 cm ³ /10min	ISO 1133

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	580000 psi	4000 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	4350 psi	30.0 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.5 %	3.5 %	ISO 527-2/1A/5

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	0.86 ft·lb/in ²	1.8 kJ/m ²	
73°F (23°C)	1.2 ft·lb/in ²	2.5 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	5.2 ft·lb/in ²	11 kJ/m ²	
73°F (23°C)	9.5 ft·lb/in ²	20 kJ/m ²	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	266 °F	130 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	194 °F	90.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	194 °F	90.0 °C	ISO 306/B50
--	311 °F	155 °C	ISO 306/A50

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	1.9 in/min	48 mm/min	ISO 3795
0.0787 In (2.00 Mm)	1.9 in/min	48 mm/min	FMVSS 302
Flame Rating			UL 94
0.06 In (1.5 Mm)	HB	HB	IEC 60695-11-10,
0.12 In (3.0 Mm)	HB	HB	-20


Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet

Hostacom FPP 40T LE K2274

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Injection Notes

Drying normally not necessary.

Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

Notes

These are typical property values not to be construed as specification limits.