

Technical Data Sheet

Hostacom EKG 239L W92535

Polypropylene Compounds

Product Description

Hostacom EKG 239L W92535 is a glass fiber reinforced PP copolymer with low melt flow rate. Product is UL listed.

Regulatory Status

For regulatory compliance information, see Hostacom EKG 239L W92535 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Europe
Application	White Goods
Market	Electrical / Electronics
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/5.0 kg)	18.5	g/10 min	ISO 1133-1
Melt Volume Flow Rate, (230 °C/5.0 kg)	18	cm ³ /10 min	ISO 1133-1
Density, (23 °C)	1.26	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	6600	MPa	ISO 178/A1
Tensile Modulus, (23 °C)	7500	MPa	ISO 527-1, -2
Tensile Stress at Yield, (23 °C)	76	MPa	ISO 527-1, -2
Tensile Strain at Yield, (23 °C)	4.5	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	16	kJ/m ²	ISO 179-1/1eA
Charpy Impact Strength - Unnotched, (23 °C)	60	kJ/m ²	ISO 179-1/1eU
Thermal			
Vicat Softening Temperature, (B50)	95	°C	ISO 306
Deflection Temperature Under Load			
(0.45 MPa, Unannealed)	158	°C	ISO 75B-1, -2
(1.80 MPa, Unannealed)	138	°C	ISO 75A-1, -2
Flammable			
Flame Rating - UL, (3.0 mm)	HB		UL 94

Notes

These are typical property values not to be construed as specification limits.