

Technical Data Sheet

Hostacom EYC 136N C12360



Polypropylene Compounds

Product Description

Hostacom EYC 136N is a 13% talc filled PP copolymer, with excellent flowability, high stiffness, high dimensional stability and excellent scratch resistance. It has been designed using the latest advancements in resin synthesis and compounding technology. This grade is delivered in customer customized colors, this Data Sheet is giving general properties, some of them may be slightly altered upon color selected.

This product is also available in other colors, new colors can be developed depending on customer requirements.

Regulatory Status

For regulatory compliance information, see Hostacom EYC 136N C12360 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status	Commercial: Active
Availability	Europe
Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Dimensional Stability; High Stiffness; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	22	g/10 min	ISO 1133-1
Density, (23 °C)	1	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2000	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	23	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	6	kJ/m ²	ISO 179-1/1eA
(-40 °C)	2	kJ/m ²	ISO 179-1/1eA
Notched Izod Impact Strength			
(23 °C)	5	kJ/m ²	ISO 180/1A
(-40 °C)	2.5	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	105	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.