

Technical Data Sheet

Hostacom HBC 181L G7V290



Polypropylene Compounds

Product Description

Hostacom HBC 181L G7V290 is a mineral filled PP homopolymer with low melt flow rate.
Product is UL listed.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

| | |
|--------------------------|--------------------------|
| Application | White Goods |
| Market | Electrical / Electronics |
| Processing Method | Injection Molding |

| Typical Properties | Nominal Value | Units | Test Method |
|---|---------------|-------------------------|---------------|
| Physical | | | |
| Melt Flow Rate, (230 °C/5.0 kg) | 11 | g/10 min | ISO 1133-1 |
| Melt Volume Flow Rate, (230 °C/5.0 kg) | 11 | cm ³ /10 min | ISO 1133-1 |
| Density, (23 °C) | 1.21 | g/cm ³ | ISO 1183-1/A |
| Mechanical | | | |
| Flexural Modulus, (23 °C, Tech. A) | 3800 | MPa | ISO 178/A1 |
| Tensile Modulus, (23 °C) | 3600 | MPa | ISO 527-1, -2 |
| Tensile Stress at Yield, (23 °C) | 33 | MPa | ISO 527-1, -2 |
| Tensile Strain at Yield, (23 °C) | 4 | % | ISO 527-1, -2 |
| Impact | | | |
| Charpy Impact Strength - Notched | | | |
| (23 °C) | 2.9 | kJ/m ² | ISO 179-1/1eA |
| (0 °C) | 1.5 | kJ/m ² | ISO 179-1/1eA |
| Charpy Impact Strength - Unnotched | | | |
| (23 °C) | 28 | kJ/m ² | ISO 179-1/1eU |
| (0 °C) | 15 | kJ/m ² | ISO 179-1/1eU |
| Thermal | | | |
| Deflection Temperature Under Load, (1.80 MPa, Unannealed) | 75 | °C | ISO 75A-1, -2 |