

Technical Data Sheet

Hostacom PF062-2C NA BLK P23943



Polypropylene Compounds

Product Description

Hostacom PF062-2C NA BLK P23943 high melt flow, 4,500 MPa flexural modulus, precolored, chemically coupled, 20% glass fiber-reinforced polypropylene homopolymer has good impact strength, high stiffness and very good moldfilling capability.

Application	Automotive Parts; Exterior Automotive Applications; Underhood
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	22	g/10 min	ISO 1133-1
Density	1.04	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus, (23 °C)	4500	MPa	ISO 178
Tensile Stress at Yield	80	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	7.0	kJ/m ²	ISO 180
Additional Information			
Mold Shrinkage			ISO 294-4

Please contact LyondellBasell for shrinkage recommendations.